



Technical Data SheetEastoflex™ E1175PL-1 Amorphous Polyolefin

Applications

- Adhesives/sealants-b&c
- Automotive
- General assembly hotmelts
- Labels non food contact
- Packaging tape
- Tape non food contact
- Wax ingredients

Key Attributes

- Broad compatibility with numerous elastomers, polymers, and other tackifying resins
- Broad temperature service range
- Convenient product form
- Excellent thermal and UV stability
- Excellent water and moisture resistance
- Low color
- Low odor

Product Description

Eastoflex[™] Amorphous Polyolefins (APOs) are characteristically saturated, low molecular weight, propylene-based olefin polymers. These products are inherently soft, tacky, and flexible, having a broad compatibility with numerous elastomers, polymers, and tackifying resins. Eastoflex[™] APOs are characterized by consistent quality, low odor, good heat stability, and low color. Eastoflex[™] E1175PL-1 is a copolymer of propylene and ethylene, pelletized and coated with a low-density polyethylene powder, having a melt viscosity of 17,500 mPa·s at 190°C.

Typical Properties

Test Method ^b	Typical Value, Units ^c
ASTM D 3236	17500 cP
ASTM E 28	125 °C (257 °F)
ASTM D 3418	-38 °C (-36 °F)
ASTM D 5	25 dmm
	1.0
	Pellets
	ASTM D 3236 ASTM E 28 ASTM D 3418

^aUnless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

Compatibility and Solubility

Broad compatibility with polyolefin polymers, waxes and hydrocarbon tackifying resins.

Packaging

Standard Package Type: Eastoflex™ E1175PL-1 is available in bags (50-lb net weight), 2,250-lb net weight per pallet. Bags are made of Polypropylene.

Pellets are coated with polyethylene to prevent blocking.

^bUnless noted otherwise, the test method is ASTM.

^cUnits are in SI or US customary units.

^dViscosity, Brookfield @ 190°C

Storage

Due to the thermoplastic behavior, pelletized material may fuse, block or lump. This can be accelerated under any of the following conditions: 1) above ambient temperature, 2) prolonged storage, 3) pressure, e.g., stacking pallets, or a combination of these conditions.

For improved handling, we therefore recommend storing the material in a temperature-controlled area, be careful with stacking material or applying pressure and preventing prolonged storage.

It should be noted that lumping does not have a negative impact on the product specifications. Due to the nature of the product, claims regarding lumping cannot be accepted.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

2/28/2018 11:35:39 AM

© 2019 Eastman Chemical Company or its subsidiaries. All rights reserved. As used herein, ® denotes registered trademark status in the U.S. only.