

# Technical Data Sheet

## Ecdel™ Elastomer 9966

### Applications

- Iv bags packaging
- Medical tubing & bags - not iv
- Pharmaceutical packaging

### Key Attributes

- Chemical resistant with low extractables
- Excellent clarity
- Excellent toughness & flexibility without plasticizers
- Heat & sterilization stability

### Product Description

Meets ISO 10993 and/or USP Class VI biocompatibility requirement.

Ecdel™ elastomers are plasticizer free copolyester elastomers (COPE) that offer clarity, toughness, flexibility, and chemical resistance needed in a variety of flexible packaging including flexible medical and pharmaceutical packaging applications. Ecdel™ elastomers are radiation, electron beam, ethylene oxide, and autoclave sterilization stable. 9966 may be injection molded or extruded. Ecdel™ elastomers may be extrusion blow molded directly into bags or extruded into film for later fabrication into bags. 9966's medium inherent viscosity makes it a good general purpose elastomer.

This product has been *CRADLE TO CRADLE CERTIFIED*™ Bronze, with Material Health Certificate, Platinum. The *CRADLE TO CRADLE CERTIFIED* mark is a registered certification mark used under license through the Cradle to Cradle Products Innovation Institute, a nonprofit organization that administers the publicly available *Cradle to Cradle Certified*™ Product Standard which provides designers and manufacturers with criteria and requirements for continually improving product materials and manufacturing processes. The *Cradle to Cradle Certified*™ Product Standard guides designers and manufacturers through a continual improvement process that looks at a product through five quality categories—material health, material reutilization, renewable energy and carbon management, water stewardship, and social fairness. A product receives an achievement level in each category—Basic, Bronze, Silver, Gold, or Platinum—with the lowest achievement level representing the product's overall mark.

The Material Health Certificate provides manufacturers with a trusted way to communicate their efforts to identify and replace chemicals of concern in their products. For more information about Cradle to Cradle certification and to obtain printable certificates for Eastman copolyesters, visit [www.cradletogether.com](#). Search for Eastman Chemical Company in *Cradle to Cradle Certified* Products Registry.

### Typical Properties

Property <sup>a</sup>	Test Method <sup>b</sup>	Typical Value, Units <sup>c</sup>
<b>Electrical Properties</b>		
Arc Resistance (tungsten electrodes)	D 495	Fails by melting
Comparative Tracking Index (CTI)	IEC 112	Fails by melting
Volume Resistivity		
In Air	D 257	10 <sup>14</sup> ohm·cm
Surface Resistivity	D 257	10 <sup>15</sup> ohms/square
Dielectric Strength, Short Time, 500 V/sec rate-of-rise		
In Air	D 149	6 kV/mm (152 V/mil)
In Oil	D 149	14 kV/mm (356 V/mil)
Dielectric Constant		
1 kHz	D 150	3.9
1 MHz	D 150	3.7
10 kHz	D 150	3.8

Dissipation Factor		
1 kHz	D 150	0.02
1 MHz	D 150	0.02
10 kHz	D 150	0.02
<b>Film Properties</b>		
Thickness of Film Tested		0.11-0.14 mm (4.5-5.5 mils)
Haze	D 1003	1 %
Gloss		
@ 45°	D 2457	85
Regular Transmittance	D 1003	94 %
Total Transmittance	D 1003	93 %
Refractive Index, $n_D$	D 542	1.51
Tensile Stress @ Yield <sup>g</sup>		
M.D.	D 882	14 MPa (2030 psi)
T.D.	D 882	12 MPa (1740 psi)
Elongation @ Break		
M.D.	D 882	>400 %
T.D.	D 882	>500 %
Tensile Modulus <sup>h</sup>	D 882	180 MPa (26000 psi)
Coefficient of Friction	D 1894	>1.0
Water Vapor Transmission Rate <sup>i</sup>	F 372	190 g/m <sup>2</sup> ·24h (12 g/100in. <sup>2</sup> ·24h)
Gas Permeability, CO <sub>2</sub> <sup>j</sup>		
@ 23°C (73°F)	D 1434	>1000 cm <sup>3</sup> ·mm/m <sup>2</sup> ·24h·atm (>2540 cm <sup>3</sup> ·mil/100in. <sup>2</sup> ·24h·atm)
Gas Permeability, O <sub>2</sub> <sup>j</sup>		
@ 30°C (86°F)	D 1434	130 cm <sup>3</sup> ·mm/m <sup>2</sup> ·24h·atm (330 cm <sup>3</sup> ·mil/100in. <sup>2</sup> ·24h·atm)
<b>Mechanical Properties</b>		
Specific Gravity	D 792	1.13
Durometer Hardness		
Shore A Scale	D 2240	95
Shore D Scale	D 2240	55
Tensile Stress @ Break <sup>d</sup>	D 638	22 MPa (3200 psi)
Tensile Stress @ Yield <sup>e</sup>	D 638	14 MPa (2030 psi)
Elongation @ Yield	D 638	38 %
Elongation @ Break	D 638	400 %
Tensile Modulus	D 638	170 MPa (24650 psi)
Flexural Modulus	D 790	150 MPa (21750 psi)
Tear Strength	D 1004	350 N (79 lbf)
Izod Impact Strength, Notched		
@ -40°C (-40°F)	D 256	40 J/m (0.75 ft·lbf/in.)
Torsional Modulus Temperature		
@ 240 MPa (35,000 psi)	D 1043	-28 °C (-18 °F)
@ 930 MPa (135,000 psi)	D 1043	<-70 °C (<-94 °F)
Water Absorption, 24 h immersion	D 570	0.4 %
<b>Thermal Properties</b>		
Inherent Viscosity	EMN-A-AC-G-V-1	1.16
Flow Rate		
(Condition 215°C/2.16 kg)	D 1238	11 g/10 min
(Condition 230°C/2.16 kg)	D 1238	18 g/10 min
Crystalline Peak Melting Point (T <sub>m</sub> )	D 3418	205 °C (400 °F)
Crystallization Temperature on Cooling (T <sub>c</sub> )	DSC	140 °C (284 °F)
Glass Transition Temperature (T <sub>g</sub> )	DSC	-40 °C (-40 °F)

Specific Heat <sup>f</sup>		
@ 100°C (212°F) - solid	DSC	1.8 kJ/kg·K (0.43 Btu/lb·°F)
@ 150°C (302°F) - solid	DSC	2.0 kJ/kg·K (0.48 Btu/lb·°F)
@ 175°C (347°F) - solid	DSC	2.3 kJ/kg·K (0.55 Btu/lb·°F)
@ 200°C (392°F) - transition	DSC	3.1 kJ/kg·K (0.74 Btu/lb·°F)
@ 225°C (437°F) - melt	DSC	2.3 kJ/kg·K (0.55 Btu/lb·°F)
@ 25°C (77°F) - solid	DSC	1.6 kJ/kg·K (0.38 Btu/lb·°F)
Heat of Fusion	E 793	27 kJ/kg (11.6 Btu/lb)
Thermal Conductivity	C 177	0.19 W/m·K (1.3 Btu·in./h·ft <sup>2</sup> ·°F)
Coefficient of Linear Thermal Expansion	D 696	15 x 10 <sup>-5</sup> /°C (mm/mm·°C) (8 x 10 <sup>-5</sup> /°F (in./in.·°F))
Brittleness Temperature	D 746	<-75 °C (<-103 °F)
Vicat Softening Temperature		
@ 1 kg load	D 1525	170 °C (338 °F)

<sup>a</sup>Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

<sup>b</sup>Unless noted otherwise, the test method is ASTM.

<sup>c</sup>Units are in SI or US customary units.

<sup>d</sup>D 412, Die C specimens, which are equivalent to ASTM D 638, Type IV specimens. Specimens were 2.0 mm (0.075 in.) thick and were tested using a crosshead speed of 500 mm (20 in.) per min.

<sup>e</sup>Injection molded ASTM D 638 Type I specimens, about 3 mm (1/8 in.) thick, were tested using a crosshead speed of 500 mm (20 in.) per min.

<sup>f</sup>For 200°C (392°F) - transition, apparent specific heat, including the effects of the heat of fusion.

<sup>g</sup>Crosshead speed, 500 mm/min (20 in./min)

<sup>h</sup>Crosshead speed, 25 mm/min (1 in./min)

<sup>i</sup>Data are based on limited testing. Test conducted at 38°C (100°F) and 100% relative humidity. Mocon values; confirmed by ASTM E 96E.

<sup>j</sup>Data are based on limited testing.

## Eastman Medical Disclaimer

It is the responsibility of the medical device manufacturer ("Manufacturer") to determine the suitability of all component parts and raw materials, including any Eastman product, used in its final product in order to ensure safety and compliance with requirements of the United States Food and Drug Administration (FDA) or other international regulatory agencies.

Eastman Chemical Company products have not been designed for nor are they promoted for end uses that would be categorized by either the United States FDA or by the International Standards Organization (ISO) as implant devices. Eastman products are not intended for use in the following applications: (1) in any bodily implant applications for greater than 30 days, based on FDA-Modified ISO-10993, Part 1 "Biological Evaluation of Medical Devices" tests (including any cosmetic, reconstructive or reproductive implant applications); (2) in any cardiac prosthetic device application, regardless of the length of time involved, including, without limitation, pacemaker leads and devices, artificial hearts, heart valves, intra-aortic balloons and control systems, and ventricular bypass assisted devices, or (3) as any critical component in any medical device that supports or sustains human life.

Eastman Chemical Company products offered for the medical market have met selected FDA-Modified ISO-10993, Part 1 "Biological Evaluation of Medical Devices" tests with human tissue contact time of 30 days or less. The tests include: cytotoxicity, sensitization, irritation or intracutaneous reactivity, systemic toxicity (acute), subchronic toxicity (sub-acute), implantation, hemocompatibility. The Manufacturer is responsible for the biological evaluation of the finished medical device.

The suitability of an Eastman Product in a given end-use environment is dependent upon various conditions including, without limitation, chemical compatibility, temperature, part design, sterilization method, residual stresses, and external loads. It is the responsibility of the Manufacturer to evaluate its final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

## Comments

Unless noted otherwise, properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

*Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product and nothing*

*herein waives any of the Seller's conditions of sale.*

1/28/2019 2:34:58 PM

© 2019 Eastman Chemical Company or its subsidiaries. All rights reserved. As used herein, ® denotes registered trademark status in the U.S. only.