

EcoPaXX® Q-HXGM24

PA410-(GF+MD)30

10% Glass Reinforced, 20% Mineral Reinforced, Heat Stabilized

Print Date: 2018-12-13

Properties	Typical Data	Unit	Test Method
Rheological properties	dry / cond		
Molding shrinkage (parallel)	0.76 / *	%	ISO 294-4
Molding shrinkage (normal)	1.25 / *	%	ISO 294-4
Mechanical properties	dry / cond		
Tensile modulus	8000 / 6000	MPa	ISO 527-1/-2
Stress at break	95 / 65	MPa	ISO 527-1/-2
Strain at break	2.5 / 3.6	%	ISO 527-1/-2
Charpy impact strength (+23°C)	35 / 40	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	30 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	4 / 5.3	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	4 / -	kJ/m ²	ISO 179/1eA
Thermal properties	dry / cond		
Melting temperature (10°C/min)	250 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	190 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	225 / *	°C	ISO 75-1/-2
Other properties	dry / cond		
Humidity absorption	1.5 / *	%	Sim. to ISO 62
Density	1340 / -	kg/m ³	ISO 1183