

EcoPaXX® Q-KG6

PA410-GF30

30% Glass Reinforced, Heat Stabilized, for E&E applications

Print Date: 2019-04-17

Properties	Typical Data	Unit	Test Method
Rheological properties	dry / cond		
Molding shrinkage (parallel)	0.6 / *	%	ISO 294-4
Molding shrinkage (normal)	1.1 / *	%	ISO 294-4
Mechanical properties	dry / cond		
Tensile modulus	9500 / 7000	MPa	ISO 527-1/-2
Stress at break	170 / 115	MPa	ISO 527-1/-2
Strain at break	4 / 5.8	%	ISO 527-1/-2
Tensile modulus (120°C)	4600 / -	MPa	ISO 527-1/-2
Stress at break (120°C)	85 / -	MPa	ISO 527-1/-2
Strain at break (120°C)	8.2 / -	%	ISO 527-1/-2
Tensile modulus (160°C)	3700	MPa	ISO 527-1/-2
Stress at break (160°C)	70	MPa	ISO 527-1/-2
Strain at break (160°C)	9.4	%	ISO 527-1/-2
Charpy impact strength (+23°C)	80 / 80	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	60 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	11 / 15	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	9 / -	kJ/m ²	ISO 179/1eA
Flexural modulus	8500 / 6300	MPa	ISO 178
Flexural strength	260 / 185	MPa	ISO 178
Thermal properties	dry / cond		
Melting temperature (10°C/min)	250 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	215 / *	°C	ISO 75-1/-2

EcoPaXX[®] Q-KG6

Print Date: 2019-04-17

Properties	Typical Data	Unit	Test Method
Temp. of deflection under load (0.45 MPa)	243 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.32 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.66 / *	E-4/°C	ISO 11359-1/-2
Electrical properties	dry / cond		
Volume resistivity	>1E13 / 2E12	Ohm*m	IEC 60093
Surface resistivity	* / 1.5E14	Ohm	IEC 60093
Electric strength	40 / 35	kV/mm	IEC 60243-1
Comparative tracking index	* / 600	V	IEC 60112
Other properties	dry / cond		
Humidity absorption	1.5 / *	%	Sim. to ISO 62
Density	1340 / -	kg/m ³	ISO 1183
Biobased content	70	% (Bio C/Total C)	ASTM D6866-12 Method B