

ForTii® F11

PPA-GF30 FR(40)

30% Glass Reinforced, PA4T, Electro-friendly, Halogen free and free of red phosphorous, Certified V-0 at 0.2mm

Print Date: 2019-10-16

ForTii® F11 has an excellent balance in flow, toughness and stiffness, enabling thin walls or complicated geometries for E&E applications. F11 is all-color VDE approved, has a high RTI electrical rating of 140°C at 0.75 mm and a CTI 600V rating to secure thermal ageing and electrical performance.

Properties	Typical Data	Unit	Test Method
Rheological properties	dry / cond		
Molding shrinkage (parallel)	0.3 / *	%	ISO 294-4
Molding shrinkage (normal)	1.2 / *	%	ISO 294-4
Mechanical properties	dry / cond		
Tensile modulus	12000 / 12000	MPa	ISO 527-1/-2
Tensile modulus (-40°C)	12500 / -	MPa	ISO 527-1/-2
Tensile modulus (80°C)	11000 / -	MPa	ISO 527-1/-2
Tensile modulus (100°C)	10000 / -	MPa	ISO 527-1/-2
Tensile modulus (120°C)	7500 / -	MPa	ISO 527-1/-2
Tensile modulus (140°C)	5700	MPa	ISO 527-1/-2
Tensile modulus (160°C)	5000	MPa	ISO 527-1/-2
Stress at break	155 / 155	MPa	ISO 527-1/-2
Stress at break (-40°C)	180 / -	MPa	ISO 527-1/-2
Stress at break (80°C)	125 / -	MPa	ISO 527-1/-2
Stress at break (100°C)	115 / -	MPa	ISO 527-1/-2
Stress at break (120°C)	100 / -	MPa	ISO 527-1/-2
Stress at break (140°C)	80	MPa	ISO 527-1/-2
Stress at break (160°C)	70	MPa	ISO 527-1/-2
Strain at break	2 / 2	%	ISO 527-1/-2
Strain at break (-40°C)	2.2 / -	%	ISO 527-1/-2

Property Data

ForTii[®] F11

Print Date: 2019-10-16

Properties	Typical Data	Unit	Test Method
Strain at break (80°C)	2 / -	%	ISO 527-1/-2
Strain at break (100°C)	2 / -	%	ISO 527-1/-2
Strain at break (120°C)	2.8 / -	%	ISO 527-1/-2
Strain at break (140°C)	3.6	%	ISO 527-1/-2
Strain at break (160°C)	3.8	%	ISO 527-1/-2
Flexural modulus	11500 / 11500	MPa	ISO 178
Flexural strength	245 / 230	MPa	ISO 178
Charpy impact strength (+23°C)	50 / 50	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	10 / 10	kJ/m ²	ISO 179/1eA

Thermal properties

dry / cond

Melting temperature (10°C/min)	325 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	305 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.2 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.65 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (parallel)	0.3	E-4/°C	ASTM D696
Coeff. of linear therm. expansion (normal)	0.35	E-4/°C	ASTM D696
Burning Behav. at 1.5 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
UL recognition	Yes / *	-	-
Burning Behav. at thickness h	V-0 / *	class	IEC 60695-11-10
Thickness tested	0.2 / *	mm	IEC 60695-11-10
UL recognition	Yes / *	-	-
Relative Temperature Index - electrical	140	°C	UL746B
RTI electrical (Thickness (1) tested)	0.75	mm	UL746B
Thermal Index 5000 hrs	163	°C	IEC 60216/ISO 527-1/-2

Electrical properties

dry / cond

Volume resistivity	>1E13 / >1E13	Ohm*m	IEC 60093
Electric strength	33 / 33	kV/mm	IEC 60243-1

Property Data

ForTii[®] F11

Print Date: 2019-10-16

Properties	Typical Data	Unit	Test Method
Comparative tracking index	600 / -	V	IEC 60112
Relative permittivity (100Hz)	4.2 / 4.2	-	IEC 60250
Relative permittivity (1 MHz)	3.9 / 3.9	-	IEC 60250
Relative permittivity (1GHz)	3.9 / 3.9	-	IEC 60250
Relative permittivity (10GHz)	3.9 / 3.8	-	IEC 60250
Other properties	dry / cond		
Humidity absorption	1.5 / *	%	Sim. to ISO 62
Density	1460 / -	kg/m ³	ISO 1183