

Technical Data Sheet

Foralyn™ E Partially Hydrogenated Rosin

Applications

- Adhesives/sealants-b&c
- Bookbinding
- Caps & lids non-food contact
- Carpet construction
- Case & carton sealing closings
- Commerical printing inks
- Film modification
- Labels non food contact
- Marine
- Packaging component films
- Packaging components non food contact
- Packaging tape
- Paints & coatings
- Polymer modification
- Protective coatings
- Road markings
- Roofing ingredients
- Solder flux
- Specialty tape
- Tape non food contact
- Tires
- Wax ingredients
- Wire/cable

Key Attributes

- Color stability
- Exceptionally light color
- Resistant to oxidation
- Wide solubility and compatibility range

Product Description

Foralyn™ E Partially Hydrogenated Rosin is a light colored, thermoplastic, acidic resin made by partially hydrogenating rosin. Because of this treatment, Foralyn™ E Partially Hydrogenated Rosin is highly resistant to oxidation and discolouration, and to changes in solubility characteristics when it is exposed to air and sunlight. Thermoplastic properties of Foralyn™ E make it particularly valuable as a plasticizer, tackifier or processing aid for reclaimed, natural and synthetic rubbers. Foralyn™ E is also suggested for the preparation of synthetic resins, pigment coatings, soldering fluxes and caulking compounds.

Typical Properties

Property ^a	Test Method ^b	Typical Value, Units ^c
General		
Ring and Ball Softening Point	ASTM E 28	75 °C
Color, Gardner ^d		2
Acid Number (mg KOH/g)		168
Refractive Index @ 100°C		1.4983
Description, Base Resin		Partially Hydrogenated Gum Rosin

^aUnless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^bUnless noted otherwise, the test method is ASTM.

^cUnits are in SI or US customary units.

^d50% resins solids in toluene or xylene

Compatibility and Solubility

Compatible with natural resins, rubber and waxes; with drying and non-drying alkyds; blown castor oil; ethylcellulose; various synthetic elastomeric and thermoplastic polymers and copolymers.

Soluble in esters, ketones, hydrocarbons, chlorinated solvents. Insoluble in water. Solubility Parameters, 50% resin concentration: 7,8-9,5 in Class I solvents - weakly hydrogen-bonded; 7,4-10,6 in Class II solvents - moderately hydrogen-bonded; 9. 5-12. 7 in Class III solvents - strongly hydrogen-bonded.

Packaging

Foralyn™ E Partially Hydrogenated Rosin is pastillated and packed in polyethylene bags of 25 kg net, and supplied on shrink-wrapped pallets of 40 bags (1000 kg) each, from Eastman's facilities in The Netherlands and from warehouses located in Europe.

Storage

Due to the thermoplastic behavior, pastillated and flaked resins may fuse, block or lump. This can be accelerated under any of the following conditions: 1) above ambient temperature, 2) prolonged storage, 3) pressure, e.g., stacking pallets, or a combination of these conditions. This is particularly applicable for low softening point resin grades.

In order to maintain the flake or pastille shape, we therefore recommend storing the material in a temperature-controlled area, be careful with stacking material or applying pressure and preventing prolonged storage.

It should be noted that lumping does not have a negative impact on the product specifications. Due to the nature of the product, claims regarding lumping cannot be accepted.

Resins are prone to gradual oxidation, some more so than others. This could result in darkening and/or it could have an adverse effect on the solubility of the resin in organic solvents or on its compatibility with polymers. Accordingly, it is recommended that strict control of inventory be observed at all times, taking care that the oldest material is used first.

Foralyn™ E Partially Hydrogenated Rosin material will remain within product specification limits for a period of at least twelve months after shipment from Eastman's production facilities in The Netherlands, provided storage conditions outlined in this data sheet are observed. However, as we can neither anticipate the conditions under which the resin is processed nor the end use applications for which it is used, we recommend that the material be tested upon receipt.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

2/28/2018 11:35:39 AM