

## Xytron™ G3080E

## PPS-I-GF30

30% Glass Reinforced, Improved Impact

Print Date: 2022-02-18

Properties	Typical Data	Unit	Test Method
<b>Rheological properties</b>		<b>Value</b>	
Molding shrinkage (parallel)	0.2	%	ISO 294-4
Molding shrinkage (normal)	0.65	%	ISO 294-4
<b>Mechanical properties</b>		<b>Value</b>	
Tensile modulus	9300	MPa	ISO 527-1/-2
Tensile modulus (120°C)	4500	MPa	ISO 527-1/-2
Tensile modulus (160°C)	2500	MPa	ISO 527-1/-2
Tensile modulus (200°C)	1900	MPa	ISO 527-1/-2
Stress at break	140	MPa	ISO 527-1/-2
Stress at break (120°C)	63	MPa	ISO 527-1/-2
Stress at break (160°C)	48	MPa	ISO 527-1/-2
Stress at break (200°C)	45	MPa	ISO 527-1/-2
Strain at break	2.5	%	ISO 527-1/-2
Strain at break (120°C)	6.8	%	ISO 527-1/-2
Strain at break (160°C)	8.5	%	ISO 527-1/-2
Strain at break (200°C)	9	%	ISO 527-1/-2
Flexural modulus	7900	MPa	ISO 178
Flexural strength	205	MPa	ISO 178
Flexural modulus (120°C)	6800	MPa	ISO 178
Flexural modulus (160°C)	2800	MPa	ISO 178
Flexural modulus (200°C)	2000	MPa	ISO 178
Charpy impact strength (+23°C)	55	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength (-30°C)	60	kJ/m <sup>2</sup>	ISO 179/1eU

Akulon®, Arnite®, Arnitel®, EcoPaXX®, ForTii®, Novamid®, Stanyl® and Xytron™ are trademarks of DSM.

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information, or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequences from the use of all such information.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. This document replaces all previous versions relating to this subject.

Copyright © DSM 2022. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of DSM.



**DSM**

BRIGHT SCIENCE. BRIGHTER LIVING.

# Xytron™ G3080E

Print Date: 2022-02-18

Properties	Typical Data	Unit	Test Method
Charpy notched impact strength (+23°C)	16	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength (-30°C)	11	kJ/m <sup>2</sup>	ISO 179/1eA
Izod impact strength (+23°C)	55	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength (+23°C)	16.5	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal properties</b>	<b>Value</b>		
Melting temperature (10°C/min)	280	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	250	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.18	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.6	E-4/°C	ISO 11359-1/-2
Coef. of lin. therm expansion, parallel, above Tg	0.14	E-4/°C	ISO 11359-1/-2
Coef. of lin. therm expansion, normal, above Tg	1.1	E-4/°C	ISO 11359-1/-2
<b>Electrical properties</b>	<b>Value</b>		
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Electric strength	36	kV/mm	IEC 60243-1
Comparative tracking index	175	V	IEC 60112
<b>Other properties</b>	<b>Value</b>		
Density	1450	kg/m <sup>3</sup>	ISO 1183

Akulon®, Arnite®, Arnitel®, EcoPaXX®, ForTii®, Novamid®, Stanyl® and Xytron™ are trademarks of DSM.

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information, or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequences from the use of all such information.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. This document replaces all previous versions relating to this subject.

Copyright © DSM 2022. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of DSM.