

Technical Data Sheet Kristalex™ 5140LV Hydrocarbon Resin

Applications

- Adhesives/sealants-b&c
- Bookbinding
- Carpet construction
- Case & carton sealing closings
- Casting wax
- Commerical printing inks
- Concrete
- Film modification
- Hygiene adhesives
- Labels non food contact
- Marine
- Packaging components non food contact
- Packaging tape
- Polymer modification
- Protective coatings
- Roofing
- Solvent borne packaging adhesives
- Specialty tape
- Tape non food contact
- Tires

Product Description

Kristalex[™] 5140LV hydrocarbon resin is a high softening point, low molecular weight resin with low organic volatile content produced by copolymerization of pure aromatic monomers. It is designed primarily for use as a modifier resin in high performance adhesives and coating compositions. In these applications, its water clear color, heat stability, and resistance to oxidation and discoloration are the advantages. In EVA-based hot melt adhesives, Kristalex[™] 5140LV is compatible with EVA grades with up to 18% vinyl acetate and is useful in formulating low-color adhesives with improved high temperature resistance. In styrenic block copolymer based adhesives, Kristalex[™] 5140LV preferentially associates with the styrenic endblocks, producing higher cohesion at temperatures up to 70°C without affecting tack and adhesion properties. Kristalex[™] 5140LV complies with many FDA regulations for applications involving direct contact with food. Compliance with a given regulation in a specific situation should be verified prior to use in a food contacting application.

Typical Properties

Property	Test Method	Typical Value, Units
General		
Ring and Ball Softening Point	ASTM E 28	140 °C
Total Organic Volatile Content ^a		<500 ppm
Color, Gardner ^e	ASTM D 6166	<1
Color ^b		
YID		7
Cloud Point ^g		
DACP		<-40 °C
MMAP		10 °C
OMS		>180 °C
Molecular Weight ^f		
M _n		1650
Mw		4650

Key Attributes

- Excellent thermal stability
- High softening point
- Low organic volatile content
- Made from pure aromatic monomer
- Water-white initial color



M _w /M _n M _z	2.8 8900
Melt Viscosity ^c	
10 poise	220 °C
100 poise	180 °C
1000 poise	160 °C
Glass Transition Temperature $(T_g)^d$	90 °C

^aTotal volatile content measure by High Performance Liquid Chromatography (HPLC)

^b50% resins solids in toluene

^cData from Kristalex™ 5140, measured by Brookfield RVT Viscometer with Thermosel

^dGlass transition temperature by differential scanning calorimetry.

^e50% in toluene.

^fMolecular weight, z-average from gel permeation chromatography, elution with THF.

^gCloud point temperature from 2:1 Vol:Vol aniline-methylcyclohexane, Eastman method.

Compatibility and Solubility

Very light color, high softening point, excellent resistance to thermal and oxidative degradation. Compatible in useful proportions with chlorinated paraffins, polystyrene, rosin and modified rosins, rosin ester, SBR, and styrenebased block copolymers. Soluble in aromatic and chlorinated hydrocarbons, esters, and ketones. Insoluble in alcohols and glycols. Limited solubility in nitroparaffins. For low or zero VOC systems Kristalex[™] 5140LV is soluble in the VOC exempt solvents t-butyl acetate and perchlorobenzenetetrafluoride (PCBTF) and will tolerate some acetone and/or methyl acetate as a diluent in solvent systems based on TBA and/or PCBTF. VOC exemptions and environmental regulations vary regionally and compliance with local standards should be verified before any claims about VOC content are made.

Packaging

Pastilles in multi-wall paper bags (50 lbs, 22. 7 kg net wt).

Storage

Due to the thermoplastic behavior, pastillated and flaked resins may fuse, block or lump. This can be accelerated under any of the following conditions: 1) above ambient temperature, 2) prolonged storage, 3) pressure, e.g., stacking pallets, or a combination of these conditions. This is particularly applicable for low softening point resin grades.

In order to maintain the flake or pastille shape, we therefore recommend storing the material in a temperaturecontrolled area, be careful with stacking material or applying pressure and preventing prolonged storage.

It should be noted that lumping does not have a negative impact on the product specifications. Due to the nature of the product, claims regarding lumping cannot be accepted.

Resins are prone to gradual oxidation, some more so than others. This could result in darkening and/or it could have an adverse effect on the solubility of the resin in organic solvents or on its compatibility with polymers. Accordingly, it is recommended that strict control of inventory be observed at all times, taking care that the oldest material is used first.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

© 2019 Eastman Chemical Company or its subsidiaries. All rights reserved. As used herein, ® denotes registered trademark status in the U.S. only.