

DSM Engineering Plastics - Property Data

Xantar[®] MX 1021

PC-unfilled

Stress Crack Modified

Properties	Typical Data	Unit	Test Method
RHEOLOGICAL PROPERTIES			
Melt volume-flow rate	4	cm ³ /10min	ISO 1133
Temperature	280	°C	ISO 1133
Load	1.2	kg	ISO 1133
Molding shrinkage (parallel)	0.6	%	ISO 294-4
MECHANICAL PROPERTIES			
Tensile modulus	2100	MPa	ISO 527-1/-2
Yield stress	52	MPa	ISO 527-1/-2
Yield strain	6	%	ISO 527-1/-2
Nominal strain at break	>50	%	ISO 527-1/-2
Puncture energy (+23°C)	16	J	ISO 6603-2
Puncture energy (-30°C)	16	J	ISO 6603-2
Flexural modulus	2200	MPa	ISO 178
Flexural strength	80	MPa	ISO 178
Izod notched impact strength (-20°C)	60	kJ/m ²	ISO 180/4A
Izod notched impact strength (23°C)	70	kJ/m ²	ISO 180/4A
THERMAL PROPERTIES			
Temp. of deflection under load (1.80 MPa)	129	°C	ISO 75-1/-2
Vicat softening temperature (50°C/h 50N)	140	°C	ISO 306
Coeff. of linear therm. expansion (parallel)	0.65	E-4/°C	ISO 11359-1/-2
Ball pressure temperature	125	°C	IEC 60695-10-2
ELECTRICAL PROPERTIES			
Electric strength	18	kV/mm	IEC 60243-1
Comparative tracking index (PLC)	2	class	UL 746A
OTHER PROPERTIES			
Density	1180	kg/m ³	ISO 1183

08.06.2004



Unlimited. **DSM**

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information.