

# Novamid® 1007J

## PA6

Injection Molding, Low Viscosity

Print Date: 2019-06-05

Properties	Typical Data	Unit	Test Method
<b>Thermal properties</b>			
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
<b>Other properties</b>			
Humidity absorption	2.8 / *	%	Sim. to ISO 62
Density	1130 / -	kg/m <sup>3</sup>	ISO 1183
<b>Material specific properties</b>			
Viscosity number	99 / *	cm <sup>3</sup> /g	ISO 307, 1157, 1628

# Novamid<sup>®</sup> 1007J

## Viscosity-shear rate

