

Novamid® 1010J

PA6

Low Viscosity, Injection Molding

Print Date: 2018-12-13

| Properties | Typical Data | Unit | Test Method |
|-------------------------------------|--------------|--------------------|---------------------|
| Thermal properties | | | |
| Melting temperature (10°C/min) | 220 / * | °C | ISO 11357-1/-3 |
| Other properties | | | |
| Humidity absorption | 2.8 / * | % | Sim. to ISO 62 |
| Density | 1130 / - | kg/m ³ | ISO 1183 |
| Material specific properties | | | |
| Viscosity number | 118 / * | cm ³ /g | ISO 307, 1157, 1628 |

Novamid[®] 1010J

Viscosity-shear rate

