

Novamid® 1015B

PA6

Low Viscosity, Injection Molding

Print Date: 2018-12-13

Properties	Typical Data	Unit	Test Method
Thermal properties			
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Other properties			
Humidity absorption	2.8 / *	%	Sim. to ISO 62
Density	1130 / -	kg/m ³	ISO 1183
Material specific properties			
Viscosity number	150 / *	cm ³ /g	ISO 307, 1157, 1628

Novamid® 1015B

Print Date: 2018-12-13

Viscosity-shear rate

