

Novamid® 1015GT30 2 NAT

PA6-I-GF30

Improved Impact, Glass Reinforced

Print Date: 2018-10-23

Properties	Typical Data	Unit	Test Method
Mechanical properties	dry / cond		
Stress at break	135 / 88	MPa	ISO 527-1/-2
Strain at break	7 / 9	%	ISO 527-1/-2
Flexural modulus	7100 / 4400	MPa	ISO 178
Flexural strength	190 / 125	MPa	ISO 178
Thermal properties	dry / cond		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Other properties	dry / cond		
Humidity absorption	1.8 / *	%	Sim. to ISO 62
Density	1330 / -	kg/m ³	ISO 1183