

Novamid® 1015GT30 BK37

PA6-I-GF30

Improved Impact, Glass Reinforced

Print Date: 2018-10-03

Properties	Typical Data	Unit	Test Method
Rheological properties	dry / cond		
Molding shrinkage [parallel]	0.5 / *	%	Sim. to ISO 294-4
Molding shrinkage [normal]	1.4 / *	%	Sim. to ISO 294-4
Mechanical properties	dry / cond		
Strain at break	7 / -	%	ISO 527-1/-2
Thermal properties	dry / cond		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Other properties	dry / cond		
Water absorption	1.8 / *	%	Sim. to ISO 62
Density	1330 / -	kg/m ³	ISO 1183