

Novamid® 3010SR NAT

PA66

Easy Molding Grade

Print Date: 2018-12-13

Properties	Typical Data	Unit	Test Method
Rheological properties	dry / cond		
Molding shrinkage [parallel]	1.8 / *	%	Sim. to ISO 294-4
Molding shrinkage [normal]	2.2 / *	%	Sim. to ISO 294-4
Mechanical properties	dry / cond		
Tensile modulus	3000 / 1200	MPa	ISO 527-1/-2
Yield stress	80 / 55	MPa	ISO 527-1/-2
Yield strain	5.5 / 20	%	ISO 527-1/-2
Nominal strain at break	31 / >50	%	ISO 527-1/-2
Flexural modulus	2900 / 1200	MPa	ISO 178
Flexural strength	117 / 70	MPa	ISO 178
Charpy impact strength (+23°C)	N / N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	4 / 13	kJ/m ²	ISO 179/1eA
Thermal properties	dry / cond		
Melting temperature (10°C/min)	260 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	67 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	196 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.8 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.8 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	V-2 / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
Burning Behav. at thickness h	V-2 / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	IEC 60695-11-10


DSM

BRIGHT SCIENCE. BRIGHTER LIVING.

Novamid[®] 3010SR NAT

Print Date: 2018-12-13

Properties	Typical Data	Unit	Test Method
Electrical properties	dry / cond		
Relative permittivity (100Hz)	4 / -	-	IEC 60250
Relative permittivity (1 MHz)	4 / -	-	IEC 60250
Dissipation factor (100 Hz)	100 / -	E-4	IEC 60250
Dissipation factor (1 MHz)	230 / -	E-4	IEC 60250
Volume resistivity	>1E13 / -	Ohm*m	IEC 60093
Surface resistivity	* / 3E14	Ohm	IEC 60093
Electric strength	26 / -	kV/mm	IEC 60243-1
Comparative tracking index	600 / -	V	IEC 60112
Other properties	dry / cond		
Humidity absorption	2.5 / *	%	Sim. to ISO 62
Density	1140 / -	kg/m ³	ISO 1183