

DSM Engineering Plastics - Property Data

Arnitel® PM650

TPE-unfilled

63 Shore D, Extrusion Grade

Properties	Typical Data	Unit	Test Method
RHEOLOGICAL PROPERTIES			
Melt volume-flow rate	4	cm ³ /10min	ISO 1133
Temperature	230	°C	ISO 1133
Load	2.16	kg	ISO 1133
MECHANICAL PROPERTIES			
Shore D Hardness (3s)	63	-	ISO 868
Tensile modulus	520	MPa	ISO 527-1/-2
Stress at break	26.8	MPa	ISO 527-1/-2
Nominal strain at break	175	%	ISO 527-1/-2
Stress at 5% strain	16.6	MPa	ISO 527-1/-2
Stress at 10% strain	22.7	MPa	ISO 527-1/-2
Stress at 50% strain	25.6	MPa	ISO 527-1/-2
Stress at 100% strain	25.5	MPa	ISO 527-1/-2
Charpy notched impact strength (+23°C)	37	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	11	kJ/m ²	ISO 179/1eA
Izod notched impact strength (23°C)	37	kJ/m ²	ISO 180/1A
THERMAL PROPERTIES			
Melting temperature (10°C/min)	221	°C	ISO 11357-1/-3
Burning Behav. at 1.6 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	IEC 60695-11-10
OTHER PROPERTIES			
Density	1260	kg/m ³	ISO 1183

13.07.2004

DSM Product

Unlimited. **DSM**

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information.