

Technical Data Sheet

Plastolyn™ 290 Hydrocarbon Resin

Applications

- Adhesives/sealants-b&c
- Bookbinding
- Carpet construction
- Case & carton sealing closings
- Casting wax
- Commercial printing inks
- Concrete
- Film modification
- Hygiene adhesives
- Labels non food contact
- Marine
- Packaging components non food contact
- Packaging tape
- Polymer modification
- Protective coatings
- Roofing
- Solvent borne packaging adhesives
- Specialty tape
- Tape non food contact
- Tires

Key Attributes

- Color stability
- Low color
- Made from purified aromatic monomers
- Very high softening point

Product Description

Plastolyn™ 290 hydrocarbon resin is a versatile, aromatic, water white, very high softening point resin for use in polymer modification, adhesives, overprint lacquers, coatings and a variety of other applications. Recommended as a flow modifier in such polymers as polyvinylchloride (PVC), acrylonitrile-butadiene-styrene (ABS) and block copolymers. Its water white color and good economy, combined with superior heat and ultraviolet light (UV) stability compared with conventional C9 hydrocarbon resins, provide formulators a new level of quality without sacrificing competitiveness.

Typical Properties

Property	Test Method	Typical Value, Units
General		
Ring and Ball Softening Point	ASTM E 28	140 °C
Color, Gardner ^b	ASTM D 6166	<1
Cloud Point ^d		
DACP		-44 °C
MMAp		8 °C
OMS		>180 °C
Molecular Weight ^c		
M _n		1350
M _w		5200
M _w /M _n		3.3
M _z		10900
Melt Viscosity		
10 poise		230 °C
100 poise		190 °C
1000 poise		165 °C
		84 °C

^aGlass transition temperature by differential scanning calorimetry.

^b50% in toluene.

^cMolecular weight, z-average from gel permeation chromatography, elution with THF.

^dCloud point temperature from 2:1 Vol:Vol aniline-methylcyclohexane, Eastman method.

Compatibility and Solubility

Soluble in aromatic and chlorinated hydrocarbons, ketones and ethers. Insoluble in aliphatic hydrocarbons, alcohols and glycols.

Packaging

Pastilles, in multiwall paper bags (50 lbs, 22.7 kg net wt).

Storage

Due to the thermoplastic behavior, pastillated and flaked resins may fuse, block or lump. This can be accelerated under any of the following conditions: 1) above ambient temperature, 2) prolonged storage, 3) pressure, e.g., stacking pallets, or a combination of these conditions. This is particularly applicable for low softening point resin grades.

In order to maintain the flake or pastille shape, we therefore recommend storing the material in a temperature-controlled area, be careful with stacking material or applying pressure and preventing prolonged storage.

It should be noted that lumping does not have a negative impact on the product specifications. Due to the nature of the product, claims regarding lumping cannot be accepted.

Resins are prone to gradual oxidation, some more so than others. This could result in darkening and/or it could have an adverse effect on the solubility of the resin in organic solvents or on its compatibility with polymers. Accordingly, it is recommended that strict control of inventory be observed at all times, taking care that the oldest material is used first.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

2/28/2018 11:35:39 AM