

# Technical Data Sheet

## Regalite™ S1100 Hydrocarbon Resin

### Applications

- Adhesives/sealants-b&c
- Bookbinding
- Carpet construction
- Case & carton sealing closings
- Casting wax
- Commercial printing inks
- Hygiene adhesives
- Labels non food contact
- Polymer modification
- Protective coatings
- Specialty tape
- Tape non food contact
- Tires

### Product Description

Regalite™ S1100 Hydrocarbon Resin is a low molecular weight fully hydrogenated water-white thermoplastic resin derived from petrochemical feedstock. This resin is especially designed as tackifier in hot melt adhesives requiring good color retention upon ageing.

### Typical Properties

Property <sup>a</sup>	Test Method <sup>b</sup>	Typical Value, Units <sup>c</sup>
<b>General</b>		
Ring and Ball Softening Point	ASTM E 28	100 °C
Color, Gardner <sup>d</sup>	ASTM D 6166	<1
Density @ 25°C		0.99 kg/dm <sup>3</sup>
Cloud Point <sup>f</sup> MMAP		80 °C
Molecular Weight <sup>e</sup>		
M <sub>n</sub>		600
M <sub>w</sub>		830
M <sub>w</sub> /M <sub>n</sub>		1.4
M <sub>z</sub>		1200
Melt Viscosity		
@ 120°C		25000 cP
@ 140°C		2500 cP
@ 160°C		600 cP

<sup>a</sup>Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

<sup>b</sup>Unless noted otherwise, the test method is ASTM.

<sup>c</sup>Units are in SI or US customary units.

<sup>d</sup>50% in toluene.

<sup>e</sup>Molecular weight, z-average from gel permeation chromatography, elution with THF.

<sup>f</sup>Cloud point temperature from 2:1 Vol:Vol aniline-methylcyclohexane, Eastman method.

## Compatibility and Solubility

Very light color, excellent adhesion, good resistance to thermal and oxidative degradation, excellent compatibility.

Soluble at all useful proportions in aliphatic, aromatic, and chlorinated hydrocarbons. Insoluble in alcohols and water.

Compatible at all ratios, or in limited but practically useful proportions, with natural and synthetic rubbers, EVA (ethylene-vinyl acetate) and EBA (Ethylene-butyl acrylate copolymers), APAO (amorphous poly-alphaolefins), SIS (styrene-isoprene-styrene) block copolymers, SBS (styrene-butadiene-styrene) block copolymers, SIBS (styrene-isoprene/butadiene-styrene) block copolymers, SEBS (styrene- ethylene/butylene- styrene) block copolymer, SEPS (styrene-ethylene/propylene-styrene) block copolymer, polyethylene, polypropylene polymers, PIB (polyisobutene) , OBC (olefinic block copolymer), mPE (metallocene catalysed polyethylene)and TPE (thermo plastic elastomers).

## Packaging

Regalite™ S1100 Hydrocarbon Resin is pastillated and packed in polyethylene bags of 20 kg net, and supplied on shrink-wrapped pallets of 50 bags (1000 kg) each, from Eastman facilities in the Netherlands and from warehouses located in Europe.

Regalite™ S1100 Hydrocarbon Resin is supplied in heated, insulated and inerted bulk containers, from Eastman facilities in The Netherlands.

## Storage

Due to the thermoplastic behavior, pastillated and flaked resins may fuse, block or lump. This can be accelerated under any of the following conditions: 1) above ambient temperature, 2) prolonged storage, 3) pressure, e.g., stacking pallets, or a combination of these conditions. This is particularly applicable for low softening point resin grades.

In order to maintain the flake or pastille shape, we therefore recommend storing the material in a temperature-controlled area, be careful with stacking material or applying pressure and preventing prolonged storage.

It should be noted that lumping does not have a negative impact on the product specifications. Due to the nature of the product, claims regarding lumping cannot be accepted.

Resins are prone to gradual oxidation, some more so than others. This could result in darkening and/or it could have an adverse effect on the solubility of the resin in organic solvents or on its compatibility with polymers. Accordingly, it is recommended that strict control of inventory be observed at all times, taking care that the oldest material is used first.

Regalite™ S1100 Hydrocarbon Resin material will remain within product specification limits, as mentioned under the heading "Product Specifications", for a period of at least twelve months after shipment from Eastman production facilities in The Netherlands, provided storage conditions outlined in this data sheet are observed. However, as we can neither anticipate the conditions under which the resin is processed nor the end use applications for which it is used, we recommend that the material be tested upon receipt.

---

*Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.*

2/28/2018 11:35:39 AM