

DSM Engineering Plastics - Property Data

Xantar® SF 2230

PC-GF30

30% Glass Reinforced, Structural Foam

Properties	Typical Data	Unit	Test Method
RHEOLOGICAL PROPERTIES			
Melt volume-flow rate	4	cm³/10min	ISO 1133
Temperature	300	°C	ISO 1133
Load	1.2	kg	ISO 1133
MECHANICAL PROPERTIES			
Tensile modulus	6500	MPa	ISO 527-1/-2
Stress at break	70	MPa	ISO 527-1/-2
Strain at break	2	%	ISO 527-1/-2
THERMAL PROPERTIES			
Temp. of deflection under load (1.80 MPa)	137	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.1	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.6 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	4.8	mm	IEC 60695-11-10
Burning Behav. 5V at thickness h	5VA	class	IEC 60695-11-20
Thickness tested	4.8	mm	IEC 60695-11-20
Oxygen index	36	%	ISO 4589-1/-2
Ball pressure temperature	125	°C	IEC 60695-10-2
ELECTRICAL PROPERTIES			
Relative permittivity (100Hz)	3.3	-	IEC 60250
Relative permittivity (1 MHz)	3.3	-	IEC 60250
Dissipation factor (100 Hz)	8	E-4	IEC 60250
Dissipation factor (1 MHz)	90	E-4	IEC 60250
Volume resistivity	>1E13	Ohm*m	IEC 60093
Surface resistivity	>1E15	Ohm	IEC 60093
OTHER PROPERTIES			
Water absorption	0.3	%	Sim. to ISO 62
Density	1430	kg/m³	ISO 1183
Density (foamed)	1110	kg/m³	ISO 1183
MATERIAL SPECIFIC PROPERTIES			
Limiting Viscosity Number	48	cm³/g	ISO 1628-4

21.07.2004



Unlimited. **DSM**

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information.