

SARLINK® 3180 is a medium hardness, multi-purpose thermoplastic elastomer featuring excellent compression set and high temperature performance. SARLINK® 3180 can be processed by blow molding, injection molding or extrusion for applications such as grips, seals, gaskets, profiles and other articles.

Typical properties*	Test method	S.I.		U.S.	
		Typical value	Units	Typical value	Units
Hardness Shore A (5 sec) Injection molded sample Extruded sample	ASTM D-2240, 5 sec. Delay 5 sec. Delay	84 80	-- --	84 80	-- --
Specific Gravity	ASTM D-792	0.95	--	0.95	--
Stress/Strain properties <u>Flow direction</u> Tensile strength Modulus at 100% Elongation at break <u>Cross direction</u> Tensile strength Modulus at 100% Elongation at break	ASTM D-412, Die C	7.1 5.1 430 9.7 4.4 673	MPa MPa % MPa MPa %	1030 740 430 1407 638 673	Psi Psi % Psi Psi %
Tear Strength <u>Cross direction</u> Unnicked	ASTM D-624, Die C	51	kN/m	291	Pli
Compression set 22h/23°C 22h/70°C 22h/100°C	ASTM D-395, Method B	28 46 52	% % %	28 46 52	% % %
Hot air aging <u>168h/150°C, Cross Direction</u> Change in hardness Retention tensile strength Retention modulus at 100% Retention elongation at break <u>1000h/125°C, Cross Direction</u> Change in hardness Retention tensile strength Retention modulus at 100% Retention elongation at break	ASTM D-573	1 91 108 85 2 92 85 90	-- % % % -- % % %	1 91 108 85 2 92 85 90	-- % % % -- % % %
Volume swell 24h/121°C Oil #3 70h/125°C Oil #3	ASTM D-471	81 95	% %	81 95	% %
Rheology <u>Apparent Shear Viscosity</u> @ 206 1/s, 200 °C	ASTM D-3835	310	Pa.s	310	Pa.s

* Tests are conducted on injection molded plaques unless indicated otherwise.

SARLINK® 3180 is a polypropylene based elastomer, which can be processed on conventional thermoplastic equipment for injection molding, extrusion and blow molding. This product has a wide processing window in most applications. Melt temperatures from 360°F to 430°F can be used. Do not exceed 450°F. Drying is recommended for extrusion and blow molding and any time the material is used from an unsealed package. Dry three (3) hours at 180°F. Drying is best accomplished in a desiccant dryer.

INJECTION MOULDING CONDITIONS			EXTRUSION CONDITIONS		
Melt temperature		360-430°F	Melt temperature		380-420°F
Barrel Temperatures	Rear Middle Front Nozzle	350-420°F 350-420°F 350-420°F 370-430°F	Barrel Temperatures	Rear Transition Metering Front Die	360-400°F 360-400°F 370-410°F 370-410°F 380-420°F
Mould temperature		50-150°F			
Screw Speed		100-200 RPM	Roll Temperature		70-120°F
Back Pressure		10-150 psi	Screen Pack		20 to 60 mesh
Screw	General Purpose 20:1 L/D ratio		Screw	General Purpose 3:1 compression ratio	

PURGING

SARLINK® 3180 has excellent melt stability. Empty the barrel for idle periods of thirty (30) minutes or longer. Purge thoroughly before and after use of this product with polyethylene or polypropylene.

RECYCLING/REGRIND

This product can be reprocessed. Physical properties are generally not degraded. Dry regrind prior to reprocessing. Drying is best accomplished in a desiccant dryer.

COLORING

The use of polyolefin based color concentrates is recommended. Apply back pressure in injection molding to disperse color.

BONDING/ASSEMBLY

Thermal bonding techniques can be used to form high strength bonds. Adhesive bonding can be achieved with specialized adhesives. Bond strength is limited due to the polypropylene base of this material.

STORAGE & HANDLING

SARLINK® 3180 is available in 55 lb. foil lined bags (up to 2,200 lbs. per pallet) or 1,100 lb. polyethylene lined gaylords. It has a storage life at normal temperatures of several years. Please refer to the Material Safety Data Sheet for this grade prior to first time handling.