

SARLINK® 3760 BLK is a low hardness multi-purpose elastomer with excellent UV-resistance. Other features are excellent compression set, heat resistance and fluid resistance. SARLINK® 3760 BLK can be processed by injection molding, blow molding and extrusion for outdoor applications such as seals, gaskets, diaphragms and weather-stripping.

Typical properties*	Test method	Typical value	Units S.I.
Density	ISO 1183	960	Kg/m ³
Hardness shore A (5 sec)	ISO 868	65	
Stress/strain properties <u>Cross direction</u> Modulus 100% Tensile strength Elongation at break	ISO 37 (II)	2.2 6.0 610	MPa MPa %
Compression set 22h/70°C	ISO 815	35	%

* Tests are conducted on injection-molded plaques unless indicated otherwise.

SARLINK® 3760 BLK is a polypropylene based elastomer which can be processed on conventional thermoplastic equipment for injection molding, extrusion and blow molding. This product has a wide processing window in most applications. Melt temperatures from 185°C to 220°C can be used. Do not exceed 260°C. Drying is recommended for extrusion and blow molding (3 hours at 80°C). Drying is best accomplished in a desiccant dryer.

INJECTION MOULDING CONDITIONS			EXTRUSION CONDITIONS		
Melt temperature		185-220°C	Melt temperature		195-215°C
Barrel Temperatures	Rear Middle Front Nozzle	180-215°C 180-215°C 180-215°C 187-220°C	Barrel Temperatures	Rear Transition Metering Front Die	180-200°C 180-205°C 187-210°C 187-210°C 195-215°C
Mould temperature		10-55°C			
Screw Speed		100-200 RPM	Roll Temperature		20-50°C
Back Pressure		0.1-1 MPa	Screen Pack		20 to 60 mesh
Screw	General Purpose		Screw	General Purpose 3:1 compression ratio	

All information supplied by or on behalf of DSM in relation to its products, whether in nature of data, recommendations or otherwise, is supported by research and believed reliable, but DSM assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use of the aforementioned information or products, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to DSM for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.

© SARLINK® is a registered trademark of DSM, The Netherlands

PURGING

SARLINK® 3760 BLK has excellent melt stability. Empty the barrel for idle periods of 30 minutes or longer. Purge thoroughly before and after use of this product with polyethylene or polypropylene.

RECYCLING/REGRIND

This product can be reprocessed. Physical properties are generally not degraded. Dry regrind prior to reprocessing. Drying is best accomplished in a desiccant dryer.

BONDING/ASSEMBLY

Thermal bonding techniques can be used to form high strength bonds. Adhesive bonding can be achieved with specialized adhesives. Adhesive bond strength is limited due to the polypropylene base of this material.

STORAGE & HANDLING

SARLINK® 3760 BLK is available in 20 kg polyethylene bags (1000 kg per pallet). It has a storage life at normal temperatures of several years. Please refer to the Material Safety Data Sheet for this grade prior to first time handling.