

Stanyl® TW272B6

(PA46+PTFE)-CF30

30% Carbon Reinforced, Heat Stabilized, Wear and Friction Modified

Print Date: 2019-10-17

Properties	Typical Data	Unit	Test Method
Rheological properties			
	dry / cond		
Molding shrinkage (parallel)	0.3 / *	%	ISO 294-4
Molding shrinkage (normal)	0.6 / *	%	ISO 294-4
Mechanical properties			
	dry / cond		
Tensile modulus	24000 / 14500	MPa	ISO 527-1/-2
Tensile modulus (120°C)	12500 / -	MPa	ISO 527-1/-2
Tensile modulus (160°C)	11000	MPa	ISO 527-1/-2
Tensile modulus (180°C)	10500	MPa	ISO 527-1/-2
Tensile modulus (200°C)	10000	MPa	ISO 527-1/-2
Stress at break	240 / 160	MPa	ISO 527-1/-2
Stress at break (120°C)	130 / -	MPa	ISO 527-1/-2
Stress at break (160°C)	110	MPa	ISO 527-1/-2
Stress at break (180°C)	100	MPa	ISO 527-1/-2
Stress at break (200°C)	90	MPa	ISO 527-1/-2
Strain at break	1.6 / 3.5	%	ISO 527-1/-2
Strain at break (120°C)	3.1 / -	%	ISO 527-1/-2
Strain at break (160°C)	3.1	%	ISO 527-1/-2
Strain at break (180°C)	3.1	%	ISO 527-1/-2
Strain at break (200°C)	3.1	%	ISO 527-1/-2
Flexural modulus	21000 / -	MPa	ISO 178
Flexural strength	340 / -	MPa	ISO 178
Charpy impact strength (+23°C)	50 / 80	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	50 / 55	kJ/m ²	ISO 179/1eU

Properties	Typical Data	Unit	Test Method
Charpy notched impact strength (+23°C)	6 / 13	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	6 / 6	kJ/m ²	ISO 179/1eA

Thermal properties

dry / cond

Melting temperature (10°C/min)	295 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	290 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.25 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.35 / *	E-4/°C	ISO 11359-1/-2

Other properties

dry / cond

Humidity absorption	2.25 / *	%	Sim. to ISO 62
Density	1350 / -	kg/m ³	ISO 1183

Tens. fatigue 8Hz, T, R=0.1 ,
dry