

Stanyl® TW275F6

PA46-GF30

30% Glass Reinforced, Heat Stabilized, Wear and Friction Modified

Print Date: 2018-12-13

Properties	Typical Data	Unit	Test Method
Rheological properties			
	dry / cond		
Molding shrinkage [parallel]	0.5 / *	%	Sim. to ISO 294-4
Molding shrinkage [normal]	1.3 / *	%	Sim. to ISO 294-4
Mechanical properties			
	dry / cond		
Stress at break	205 / 115	MPa	ISO 527-1/-2
Stress at break (120°C)	110 / -	MPa	ISO 527-1/-2
Stress at break (160°C)	100	MPa	ISO 527-1/-2
Stress at break (180°C)	95	MPa	ISO 527-1/-2
Stress at break (200°C)	90	MPa	ISO 527-1/-2
Strain at break	3.5 / 7	%	ISO 527-1/-2
Strain at break (120°C)	8.4 / -	%	ISO 527-1/-2
Strain at break (160°C)	8.9	%	ISO 527-1/-2
Strain at break (180°C)	9.1	%	ISO 527-1/-2
Strain at break (200°C)	9.4	%	ISO 527-1/-2
Flexural modulus	9000 / 6000	MPa	ISO 178
Charpy impact strength (+23°C)	75 / 100	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	60 / 70	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	10 / 18	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	9 / 9	kJ/m ²	ISO 179/1eA
Izod notched impact strength (+23°C)	10 / 18	kJ/m ²	ISO 180/1A
Izod notched impact strength (-40°C)	9 / 9	kJ/m ²	ISO 180/1A

Property Data

Stanyl[®] TW275F6

Print Date: 2018-12-13

Properties	Typical Data	Unit	Test Method
Melting temperature (10°C/min)	295 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	285 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	290 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.25 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.6 / *	E-4/°C	ISO 11359-1/-2

Other properties

dry / cond

Humidity absorption	2.5 / *	%	Sim. to ISO 62
Density	1430 / -	kg/m ³	ISO 1183