

Stanyl® ForTii™ LDS51 (NC1119B)

PA4T-GF30 FR(40)

30% Glass Reinforced, Flame Retardant, Halogen free and free of red phosphorous, Laser Direct Structuring (LDS)

Properties	Typical Data	Unit	Test Method
Mechanical properties			
	dry / cond		
Tensile modulus	11000/11000	MPa	ISO 527-1/-2
Stress at break	120/120	MPa	ISO 527-1/-2
Strain at break	1.6/1.6	%	ISO 527-1/-2
Charpy impact strength (+23°C)	25/-	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	3/-	kJ/m ²	ISO 179/1eA
Thermal properties			
	dry / cond		
Melting temperature (10°C/min)	325/*	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	290/*	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.3	E-4/°C	ASTM D696
Coeff. of linear therm. expansion (normal)	0.4	E-4/°C	ASTM D696
Burning Behav. at thickness h	V-0/*	class	IEC 60695-11-10
Thickness tested	0.8/*	mm	IEC 60695-11-10
Electrical properties			
	dry / cond		
Volume resistivity	>1E13/>1E13	Ohm*m	IEC 60093
Comparative tracking index	400/-	-	IEC 60112
Other properties			
	dry / cond		
Density	1580/-	kg/m ³	ISO 1183

16.10.2014

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information. Typical values are indicative only and are not to be construed as being binding specifications.

