



组件 - 塑料
UL 档案号: E47960

DSM ENGINEERING MATERIALS B V
URMONDERBAAN 22
GELEEN, 6167 RD Netherlands



Stanyl: TE351

Polyamide 46 (PA46), pellets

可燃性	值	测试方法
UL 阻燃等级		UL 94
0.75 mm, NC, BK	V-0	IEC 60695-11-10, -20
1.5 mm, NC, BK	V-0	
3.0 mm, NC, BK	V-0	
电气性能	值	测试方法
热丝引燃 (HWI)		UL 746
0.75 mm	PLC 4	
1.5 mm	PLC 2	
3.0 mm	PLC 0	
高电弧燃烧指数(HAI)		UL 746
0.75 mm	PLC 0	
1.5 mm	PLC 0	
3.0 mm	PLC 0	
相比耐漏电起痕指数(CTI)	PLC 2	UL 746
高电压电弧起痕速率 (HVTR)	PLC 1	UL 746
耐电弧性	PLC 7	ASTM D495
热性能	值	测试方法
RTI Elec		UL 746
0.75 mm	65.0 °C	
1.5 mm	130 °C	
3.0 mm	130 °C	
RTI Imp		UL 746
0.75 mm	65.0 °C	
1.5 mm	65.0 °C	
3.0 mm	65.0 °C	
RTI		UL 746
0.75 mm	65.0 °C	
1.5 mm	65.0 °C	
3.0 mm	65.0 °C	
Ball Pressure Test (270°C, 3.00 mm)	通过	IEC 60695-10-2