

Arnite® TM4 440

(PBT+PET)-MD20

20% Mineral Reinforced

Print Date: 2016-09-28

Properties	Typical Data	Unit	Test Method
Rheological properties			
Melt volume-flow rate	34	cm ³ /10min	ISO 1133
Temperature	270	°C	ISO 1133
Load	2.16	kg	ISO 1133
Molding shrinkage [normal]	1.7	%	Sim. to ISO 294-4
Molding shrinkage [parallel]	1.4	%	Sim. to ISO 294-4
Mechanical properties			
Tensile modulus	5100	MPa	ISO 527-1/-2
Stress at break	57	MPa	ISO 527-1/-2
Strain at break	1.9	%	ISO 527-1/-2
Charpy impact strength (+23°C)	31	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	1.8	kJ/m ²	ISO 179/1eA
Thermal properties			
Melting temperature (10°C/min)	225	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	100	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	195	°C	ISO 75-1/-2
Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	IEC 60695-11-10
Other properties			
Water absorption	0.35	%	Sim. to ISO 62
Humidity absorption	0.15	%	Sim. to ISO 62

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information. Typical values are indicative only and are not to be construed as being binding specifications.


Property Data

Arnite[®] TM4 440

Print Date: 2016-09-28

Properties	Typical Data	Unit	Test Method
Density	1480	kg/m ³	ISO 1183

Viscosity-shear rate



All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information. Typical values are indicative only and are not to be construed as being binding specifications.