



组件 - 塑料
UL 档案号: E43392

DSM ENGINEERING PLASTICS INC
2267 W MILL RD, EVANSVILLE IN 47732



Arnite: TV4 261

Polybutylene Terephthalate (PBT), pellets

可燃性	值	测试方法
UL 阻燃等级		
0.71 mm, ALL	HB	UL 94
1.5 mm, ALL	HB	UL 94
3.0 mm, ALL	HB	UL 94
3.0 mm, ALL	HB40	IEC 60695-11-10, -20
0.71 mm, ALL	HB75	IEC 60695-11-10, -20
1.5 mm, ALL	HB75	IEC 60695-11-10, -20
电气性能	值	测试方法
热丝引燃 (HWI)		UL 746
0.71 mm	PLC 3	
1.5 mm	PLC 2	
3.0 mm	PLC 2	
高电弧燃烧指数(HAI)		UL 746
0.71 mm	PLC 1	
1.5 mm	PLC 1	
3.0 mm	PLC 2	
相比耐漏电起痕指数(CTI)	PLC 1	UL 746
介电强度	42 kV/mm	ASTM D149 IEC 60243-1
高电压电弧起痕速率 (HVTR)	PLC 2	UL 746
体积电阻率	1.0E+10 ohms-cm	ASTM D257 IEC 60093
耐电弧性	PLC 5	ASTM D495
热性能	值	测试方法
RTI Elec		UL 746
0.71 mm	140 °C	
1.5 mm	140 °C	
3.0 mm	140 °C	
RTI Imp		UL 746
0.71 mm	130 °C	
1.5 mm	130 °C	
3.0 mm	130 °C	
RTI		UL 746
0.71 mm	140 °C	
1.5 mm	140 °C	
3.0 mm	140 °C	
物理性能	值	测试方法
Dimensional Stability	0.60 %	ASTM D1042 ISO 2796