

Technical Data Sheet

Tenite™ Butyrate 264A3720013 Clear Trsp

Applications

- Sporting equipment
- Tools

Product Description

Tenite™ cellulosic plastics are noted for their excellent balance of properties - toughness, hardness, strength, surface gloss, clarity, and a warm feel. The mechanical properties of Tenite™ cellulosic plastics differ with plasticizer levels. Lower plasticizer content yields a harder surface, higher heat resistance, greater rigidity, higher tensile strength, and better dimensional stability. Higher plasticizer content increases impact strength. Tenite™ cellulosic plastics are available in natural, clear, selected ambers, or smoke transparents and black translucent. Color concentrates are available in let-down ratios from 10:1 to 40:1. Tenite™ Cellulose Acetate Butyrate 264-13 has a plasticizer level of 13%.

Typical Properties

Property ^a	Test Method ^b	Typical Value, Units ^c
General		
Plasticizer		13 %
Specific Gravity	D 792	1.18
Mechanical Properties		
Tensile Stress @ Yield	D 638	29.0 MPa (4200 psi)
Tensile Stress @ Break	D 638	39.3 MPa (5700 psi)
Elongation @ Break	D 638	50 %
Flexural Modulus	D 790	1241 MPa (1.80 x 10 ⁵ psi)
Flexural Yield Strength	D 790	39.3 MPa (5700 psi)
Rockwell Hardness, R Scale	D 785	59
Izod Impact Strength, Notched		
@ 23°C (73°F)	D 256	283 J/m (5.3 ft·lbf/in.)
@ -40°C (-40°F)	D 256	101 J/m (1.9 ft·lbf/in.)
Miscellaneous Butyrate Properties		
Refractive Index, n _D	D 542	1.46-1.49
Light Transmission ^e	E 308	>90 %
Haze ^e	D 1003	<8.5 %
Specific Heat		
@ 23°C (73°F)	DSC	1.26-1.67 kJ/kg·K (0.301-0.399 Btu/lb·°F)
Thermal Conductivity	C 177	0.17-0.33 W/m·K (1.2-2.3 Btu·in./h·ft ² ·°F)
Coefficient of Linear Thermal Expansion	D 696	11-17 x 10 ⁻⁵ /°C (mm/mm·°C) (6-9 x 10 ⁻⁵ /°F (in./in·°F))
Mold Shrinkage	D 955	0.2-0.6 %
Dielectric Strength	D 149	11.8-18.7 kV/mm (300-475 V/mil)
Dielectric Constant		
1 MHz	D 150	3.3-3.8
Dissipation Factor		
1 MHz	D 150	0.01-0.15
Volume Resistivity	D 257	10 ¹³ -10 ¹⁵ ohm·cm

Permanence Properties		
Water Absorption, 24 h immersion	D 570	1.4 %
Soluble Matter Loss	D 570	0.1 %
Weight Loss on Heating [72 hours @ 80°C (176°F)]	D 707	0.6 %
Thermal Properties		
Deflection Temperature ^d		
@ 0.455 MPa (66 psi)	D 648	81 °C (178 °F)
@ 1.82 MPa (264 psi)	D 648	69 °C (156 °F)
Vicat Softening Temperature ^d	D 1525	100 °C (212 °F)

^aUnless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^bUnless noted otherwise, the test method is ASTM.

^cUnits are in SI or US customary units.

^dConditioned 4 hours @ 70°C (158°F)

^e1.52-mm (0.06-in.) specimen thickness

Characteristics

Formula 264 - base.

Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

7/19/2018 9:41:45 AM