

DSM Engineering Plastics - Property Data

Stamylan® UH 610

PE-unfilled

Properties	Typical Data	Unit	Test Method
RHEOLOGICAL PROPERTIES			
Elongational Stress F(150/10)	0.53	MPa	ISO 11542-2/A
MECHANICAL PROPERTIES			
Tensile modulus	650	MPa	ISO 527-1/-2
Yield stress	19	MPa	ISO 527-1/-2
Yield strain	11	%	ISO 527-1/-2
Nominal strain at break	>50	%	ISO 527-1/-2
Abrasion resistance	80	%	DIN 16972
Charpy double-notched impact strength (23°C)	110	kJ/m ²	ISO 11542-2/B
THERMAL PROPERTIES			
Melting temperature (10°C/min)	133	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Density	930	kg/m ³	ISO 1183
Apparent density	480	kg/m ³	ISO 60
Average particle size	150	m-6	-
MATERIAL SPECIFIC PROPERTIES			
Viscosity number	3650	cm ³ /g	ISO 307, 1157, 1628
Average molecular weight	8.70E6	g/mol	-

02.04.2004



Unlimited. DSM

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information.