

# Pocan<sup>®</sup> ECOB3233HRLT

## PBT-GF30

30% Glass Reinforced, Injection Molding, Hydrolysis resistant, Laser Weldable, Laser Transparent Black, Recycled Content

Print Date: 2024-09-17

### Sustainability

Mass balanced  
Recycled based

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
<b>RHEOLOGICAL PROPERTIES</b>			
	VALUE		
Molding shrinkage (normal)	0.8	%	ISO 294-4
Molding shrinkage (parallel)	0.3	%	ISO 294-4
<b>MECHANICAL PROPERTIES</b>			
	VALUE		
Tensile modulus	10000	MPa	ISO 527-1/-2
Stress at break	140	MPa	ISO 527-1/-2
Strain at break	2.8	%	ISO 527-1/-2
Flexural modulus	9600	MPa	ISO 178
Flexural strength	230	MPa	ISO 178
Flexural strain at flexural strength	3.2	%	ISO 178-A
Charpy impact strength (+23°C)	60	kJ/m <sup>2</sup>	ISO 179/1eU
Izod impact strength (+23°C)	53	kJ/m <sup>2</sup>	ISO 180/1U
<b>THERMAL PROPERTIES</b>			
	VALUE		
Melting temperature (10°C/min)	225	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	190	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	215	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.2	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1	E-4/°C	ISO 11359-1/-2

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

## Property Data

# Pocan<sup>®</sup> ECOB3233HRLT

Print Date: 2024-09-17

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
<b><i>ELECTRICAL PROPERTIES</i></b>			
Comparative tracking index	275	V	IEC 60112
<b><i>OTHER PROPERTIES</i></b>			
Density	1520	kg/m <sup>3</sup>	ISO 1183
<b><i>PROCESSING RECOMMENDATIONS</i></b>			
Drying temperature circulating air dryer	120	°C	
Drying time circulating air dryer	4-8	h	
Residual moisture content	0.00-0.02	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	260-280	°C	
Mold temperature	60-80	°C	

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.