



TotalEnergies

Refining & Chemicals
Polymers

+135-3858-6433 (GuangDong)
+188-1699-6168 (ShangHai)
+852-6957-5415 (HongKong)

Polyethylene EVA 1003 VN 4

Technical data sheet
Ethylene Vinyl Acetate Copolymer BLOWN FILM
Produced in Europe

Description

EVA 1003 VN 4 is made by a high pressure tubular process.
Grade for flexible films, with very high transparency and outstanding mechanical properties.

Application examples: High strength stretch film, green house film, film for food packaging (coextrusion), stretch hood.

Characteristics

Property	Method	Unit	Typical value
Melt Flow Rate (190°C/2.16 kg)	ISO 1133	Mpa	0.4
VA Content	TotalEnergies	Mpa	13.5
Melting temperature	ISO 11357	%	92
Vicat temperature	ISO 306	N/mm	74
Elasticity Modulus	ISO 527-2	G	70
Density	ISO 1183	%	0.935

Values indicated are typical for this product. VA Content and MFR are properties routinely measured during "the standard quality control procedure". The other figures are generated by tests not included in the "standard quality control procedure" and are given for information only. Data are not intended for specification purposes.



TotalEnergies

Refining & Chemicals
Polymers

+135-3858-6433 (GuangDong)
+188-1699-6168 (ShangHai)
+852-6957-5415 (HongKong)

Polyethylene EVA 1003 VN 4

Blown film properties

These values have been measured on a 40 µm blown film.

Property	Method	Unit	Typical value (*)
Tensile Strength at Yield MD/TD	ISO 527-3	Mpa	6.5/5
Tensile Strength at Break MD/TD	ISO 527-3	Mpa	38/38
Elongation at Break MD/TD	ISO 527-3	%	310/590
Elmendorf MD/TD	ISO 6383-2	N/mm	13/28
Dart test	ISO 7765-1	G	650
Haze	ISO 14782	%	2.5

(*) Figures stated hereabove are obtained using laboratory test specimens produced with the following extrusion conditions: 45 mm screw diameter, L/D = 30, die diameter = 120 mm, die gap = 1.4 mm, BUR = 2.5:1, temperature = 180° C.

Polyethylene