



**TotalEnergies**

Refining & Chemicals  
Polymers

+135-3858-6433 (GuangDong)  
+188-1699-6168 (ShangHai)  
+852-6957-5415 (HongKong)

# Polypropylene PPH 3060

Technical data sheet  
Polypropylene – Homopolymer  
Produced in Europe

## Description

Polypropylene PPH 3060 is homopolymer with a Melt Flow Index of 1.8 g/10 min.

Polypropylene PPH 3060 is characterized by a low fluidity for continuous extrusion of strapping, rope fibres and high tenacity tapes for bags.

It is also well designed for blow-molding or extrusion-thermoforming

## Characteristics

	Method	Unit	Typical Value
<b>Rheological properties</b>			
Melt Flow Index 230°C/2.16 kg	ISO 1133	g/10 min	1.8
<b>Mechanical properties</b>			
Tensile Strength at Yield	ISO 527-2	MPa	35
Elongation at Yield	ISO 527-2	%	10
Tensile modulus	ISO 527-2	MPa	1400
Flexural modulus	ISO 178	MPa	1300
Izod Impact Strength (notched) at 23°C	ISO 180	kJ/m <sup>2</sup>	6
Charpy Impact Strength (notched) at 23°C	ISO 179	kJ/m <sup>2</sup>	7
Hardness Rockwell - R-scale	ISO 2039-2		90
<b>Thermal properties</b>			
Melting Point	ISO 3146	°C	165
Vicat Softening Point	ISO 306	°C	
50N-50°C per hour			87
10N-50°C per hour			152
Heat Deflection Temperature	ISO 752	°C	
1.80 MPa - 120°C per hour			55
0.45 MPa - 120°C per hour			100
<b>Other physical properties</b>			
Density	ISO 1183	g/cm <sup>3</sup>	0.905
Bulk Density	ISO 1183	g/cm <sup>3</sup>	0.525

Polypropylene