



**TotalEnergies**

Refining & Chemicals  
Polymers

+135-3858-6433 (GuangDong)  
+188-1699-6168 (ShangHai)  
+852-6957-5415 (HongKong)

## Polypropylene PPH 4069

Technical data sheet  
Polypropylene – Homopolymer  
Produced in Europe

### Description

Polypropylene PPH 4069 is homopolymer with a Melt Flow Index of 4 g/10 min.

Polypropylene PPH 4069 is intended for extrusion of high tenacity staple fibres for nonwoven applications. It exhibits excellent spinning properties.

Polypropylene PPH 4069 has an anti gas-fading formulation to reduce yellowing in fibres.

### Characteristics

	Method	Unit	Typical Value
<b>Rheological properties</b>			
Melt Flow Index 230°C/2.16 kg	ISO 1133	g/10 min	4
<b>Mechanical properties</b>			
Tensile Strength at Yield	ISO 527-2	MPa	35
Elongation at Yield	ISO 527-2	%	10
Tensile modulus	ISO 527-2	MPa	1550
Flexural modulus	ISO 178	MPa	1450
Izod Impact Strength (notched) at 23°C	ISO 180	kJ/m <sup>2</sup>	3.5
Charpy Impact Strength (notched) at 23°C	ISO 179	kJ/m <sup>2</sup>	4.5
Hardness Rockwell - R-scale	ISO 2039-2		95
<b>Thermal properties</b>			
Melting Point	ISO 3146	°C	164
Vicat Softening Point	ISO 306	°C	
50N-50°C per hour			85
10N-50°C per hour			150
Heat Deflection Temperature	ISO 752	°C	
1.80 MPa - 120°C per hour			55
0.45 MPa - 120°C per hour			100
<b>Other physical properties</b>			
Density	ISO 1183	g/cm <sup>3</sup>	0.905
Bulk Density	ISO 1183	g/cm <sup>3</sup>	0.525

Polypropylene