



**TotalEnergies**

Refining & Chemicals  
Polymers

+135-3858-6433 (GuangDong)  
+188-1699-6168 (ShangHai)  
+852-6957-5415 (HongKong)

# Polypropylene PPC 12642

Technical data sheet  
Polypropylene – Heterophasic Copolymer  
Produced in Europe

## Description

Polypropylene PPC 12642 is a nucleated antistatic heterophasic copolymer with high Melt Flow Index of 70 g/10 min and good mechanical properties.

Polypropylene PPC 12642 has been developed for high speed injection moulding of thin walled packaging containers.

We hereby confirm that we do not use peroxide in the manufacturing of the above-mentioned Product.

## Characteristics

	Method	Unit	Typical Value
<b>Rheological properties</b>			
Melt Flow Index 230°C/2.16 kg	ISO 1133	g/10 min	70
<b>Mechanical properties</b>			
Tensile Strength at Yield	ISO 527-2	MPa	27
Elongation at Yield	ISO 527-2	%	5
Tensile modulus	ISO 527-2	MPa	1600
Flexural modulus	ISO 178	MPa	1500
Izod Impact Strength (notched)	ISO 180	kJ/m <sup>2</sup>	
at 23°C			6.5
at -20°C			4
Charpy Impact Strength (notched)	ISO 179	kJ/m <sup>2</sup>	
at 23°C			6
at -20°C			4.5
Hardness Rockwell - R-scale	ISO 2039-2		100
<b>Thermal properties</b>			
Melting Point	ISO 3146	°C	165
Vicat Softening Point	ISO 306	°C	
50N-50°C per hour			80
10N-50°C per hour			148
Heat Deflection Temperature	ISO 752	°C	
1.80 MPa - 120°C per hour			55
0.45 MPa - 120°C per hour			100
<b>Other physical properties</b>			
Density	ISO 1183	g/cm <sup>3</sup>	0.905
Bulk Density	ISO 1183	g/cm <sup>3</sup>	0.525

Polypropylene