



**TotalEnergies**

Refining & Chemicals  
Polymers

+135-3858-6433 (GuangDong)  
+188-1699-6168 (ShangHai)  
+852-6957-5415 (HongKong)

# Polypropylene PPC 3640

Technical data sheet  
Polypropylene – Heterophasic Copolymer  
Produced in Europe

## Description

Polypropylene PPC 3640 is a nucleated heterophasic copolymer with a Melt Flow Index of 1.3 g/10 min. Polypropylene PPC 3640 is characterized by improved stiffness, creep resistance and high impact resistance. Polypropylene PPC 3640 has been developed specifically for the extrusion of corrugated cardboard, corrugated and twin walled pipes, conduit pipe and other extrusion applications.

## Characteristics

	Method	Unit	Typical Value
<b>Rheological properties</b>			
Melt Flow Index 230°C/2.16 kg	ISO 1133	g/10 min	1.3
<b>Mechanical properties</b>			
Tensile Strength at Yield	ISO 527-2	MPa	27
Elongation at Yield	ISO 527-2	%	6
Tensile modulus	ISO 527-2	MPa	1350
Flexural modulus	ISO 178	MPa	1300
Izod Impact Strength (notched)	ISO 180	kJ/m <sup>2</sup>	
at 23°C			>50
at -20°C			7
Charpy Impact Strength (notched)	ISO 179	kJ/m <sup>2</sup>	
at 23°C			>50
at -20°C			8
Hardness Rockwell - R-scale	ISO 2039-2		82
<b>Thermal properties</b>			
Melting Point	ISO 3146	°C	165
Vicat Softening Point	ISO 306	°C	
50N-50°C per hour			75
10N-50°C per hour			150
Heat Deflection Temperature	ISO 752	°C	
1.80 MPa - 120°C per hour			52
0.45 MPa - 120°C per hour			92
<b>Other physical properties</b>			
Density	ISO 1183	g/cm <sup>3</sup>	0.905
Bulk Density	ISO 1183	g/cm <sup>3</sup>	0.525

Polypropylene