

## Description

Circular Compound rPPC06NAT is a low MFR high stiffness and high impact polypropylene of light grey color, containing at least 50% of post-consumer recycled (PCR) originating from post consumer household waste collected in Western European countries.

Circular Compound rPPC06NAT is especially suited for injection molding applications. It is available in 1000 kg big-bag on 110x110 pallet or in bulk.

Circular Compound rPPC06NAT is not intended for food contact, pharmaceutical or medical applications.

## Characteristics

	Method	Unit	Typical Value
<b>Rheological properties</b>			
Melt Flow Index 230°C/2.16 kg	ISO 1133	g/10 min	6
<b>Mechanical properties</b>			
Flexural modulus	ISO 178	MPa	1600
Charpy Impact Strength (notched), 23°C	ISO 179	kJ/m <sup>2</sup>	8
<b>Physical properties</b>			
Recycled content	EN15343	%	>50
Colour	RAL		ca. 7042
Density	ISO 1183	g/cm <sup>3</sup>	< 0.980
Ash content	ISO3451-1	%	< 12
Humidity @110°C		%	< 0,1