

Description

Polypropylene PPH 7062 is an antistatic homopolymer with a Melt Flow Index of 12 g/10 min.

Polypropylene PPH 7062 is intended for injection moulding applications of boxes, closures and household articles.

Characteristics

	Method	Unit	Typical Value
Rheological properties			
Melt Flow Index 230°C/2.16 kg	ISO 1133	g/10 min	12
Mechanical properties			
Tensile Strength at Yield	ISO 527-2	MPa	32
Elongation at Yield	ISO 527-2	%	10
Tensile modulus	ISO 527-2	MPa	1550
Flexural modulus	ISO 178	MPa	1450
Izod Impact Strength (notched) at 23°C	ISO 180	kJ/m ²	3.5
Charpy Impact Strength (notched) at 23°C	ISO 179	kJ/m ²	4.5
Hardness Rockwell - R-scale	ISO 2039-2		95
Thermal properties			
Melting Point	ISO 3146	°C	165
Vicat Softening Point	ISO 306	°C	
50N-50°C per hour			87
10N-50°C per hour			152
Heat Deflection Temperature	ISO 752	°C	
1.80 MPa - 120°C per hour			55
0.45 MPa - 120°C per hour			100
Other physical properties			
Density	ISO 1183	g/cm ³	0.905
Bulk Density	ISO 1183	g/cm ³	0.525