

## TEKNORAPEX ±0 APEX® 121 121

Teknor Apex Company - Flexible Polyvinyl Chloride

Monday, August 26, 2019

General Information					
General					
Material Status	Commercial: Active				
Availability	<ul><li> Africa &amp; Middle East</li><li> Asia Pacific</li></ul>	<ul><li>Europe</li><li>Latin America</li></ul>	North America		
Features	UV Resistant				
Uses	Telephone Drop Wire Insulation      Telephone Drop Wire Jacketing				
Agency Ratings	REA Unspecified Rating				
RoHS Compliance	RoHS Compliant				
Appearance	Opaque				
Forms	Pellets				

ASTM & ISO Properties <sup>1</sup>					
Physical	Nominal Value	Unit	Test Method		
Density / Specific Gravity	1.26		ASTM D792		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Break)	2500	psi	ASTM D638		
Tensile Elongation (Break)	360	%	ASTM D638		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore A, 15 sec)	83		ASTM D2240		
Thermal	Nominal Value	Unit	Test Method		
Continuous Use Temperature	194	°F	ASTM D794		
Brittleness Temperature	-59.8	°F	ASTM D746		
Flammability	Nominal Value	Unit	Test Method		
Oxygen Index	27	%	ASTM D2863		

## Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

Revision Date: 12/12/2013

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.