

APEX® 32022RV-65NT CBL B8 NP

Teknor Apex Company - Flexible Polyvinyl Chloride

Tuesday, August 27, 2019

General				
Material Status	Commercial: Active			
Availability	 Africa & Middle East Asia Pacific	EuropeLatin America	North America	
Features	BPA FreeE-beam SterilizableEthylene Oxide Sterilizable	 Latex Free No Animal Derived Components Non-Phthalate - Citrate Plasticizer 	 Plasticized Radiation (Gamma) Resistan Radiation Sterilizable 	
Agency Ratings	• EC 1907/2006 (REACH)	EC 1907/2006 (REACH) OEHHA (California) Proposition 65		
RoHS Compliance	RoHS Compliant			
Forms	Pellets			
Processing Method	Injection Molding			

General Information

<u>+135-3858-6433</u> +188-1699-6168 +852-695-75415

ASTM & ISO Properties ¹				
Physical	Nominal Value	Unit	Test Method	
Density / Specific Gravity	1.22		ASTM D792	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength			ASTM D638	
50% Strain	445	psi		
100% Strain	765	psi		
300% Strain	1710	psi		
Tensile Strength (Break)	2020	psi	ASTM D638	
Tensile Elongation (Break)	390	%	ASTM D638	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness			ASTM D2240	
Shore A, 15 sec, Operating Stand	60			
Shore A, 15 sec, Hand Held	65			

Additional Information

EXAMPLE INJECTION MOLDING APPLICATIONS Adaptors **Blood Pressure Bulbs** Canulae Caps Connectors Drip/Sight Chambers Ear Protection Endotracheal Airway Cuffs Luers Mouthpieces Oxygen Masks Personal Safety Goggles **Resuscitation Bags** Suction Bulbs Syringe Bulbs Valves

Data Sheet Applies to Color(s) Listed Below: Clear Blue B8 NP (1136789)

<u>+135-3858-6433</u> +188-1699-6168

APEX® 32022RV-65NT CBL B8 N

Teknor Apex Company - Flexible Polyvinyl Chloride

Processing Information			
Extrusion	Nominal Value Unit		
Melt Temperature	325 to 345 °F		

Notes

¹ Typical properties: these are not to be construed as specifications.

Revision Date: 8/9/2019

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.