

APEX® 32022RV-80NT CBL B8 NP

Teknor Apex Company - Flexible Polyvinyl Chloride

Tuesday, August 27, 2019

General Information

General

| | | | |
|-------------------|--|---|--|
| Material Status | • Commercial: Active | | |
| Availability | • Africa & Middle East • Asia Pacific | • Europe • Latin America | • North America |
| Features | • BPA Free • E-beam Sterilizable • Ethylene Oxide Sterilizable | • Latex Free • No Animal Derived Components • Non-Phthalate - Citrate Plasticizer | • Non-Phthalate Plasticizer • Radiation (Gamma) Resistant • Radiation Sterilizable |
| Agency Ratings | • EC 1907/2006 (REACH) | • OEHHA (California) Proposition 65 | |
| RoHS Compliance | • RoHS Compliant | | |
| Forms | • Pellets | | |
| Processing Method | • Injection Molding | | |

ASTM & ISO Properties ¹

| Physical | Nominal Value | Unit | Test Method |
|----------------------------------|---------------|------|-------------|
| Density / Specific Gravity | 1.25 | | ASTM D792 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength | | | ASTM D638 |
| 50% Strain | 790 | psi | |
| 100% Strain | 1300 | psi | |
| 300% Strain | 2220 | psi | |
| Tensile Strength (Break) | 2650 | psi | ASTM D638 |
| Tensile Elongation (Break) | 330 | % | ASTM D638 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness | | | ASTM D2240 |
| Shore A, 15 sec, Operating Stand | 74 | | |
| Shore A, 15 sec, Hand Held | 80 | | |

Additional Information

EXAMPLE INJECTION MOLDING APPLICATIONS

Adaptors
 Blood Pressure Bulbs
 Canulae
 Caps
 Connectors
 Drip/Sight Chambers
 Ear Protection
 Endotracheal Airway Cuffs
 Luers
 Mouthpieces
 Oxygen Masks
 Personal Safety Goggles
 Resuscitation Bags
 Suction Bulbs
 Syringe Bulbs
 Valves

Data Sheet Applies to Color(s) Listed Below:
 Clear Blue B8 NP (1136786)

+135-3858-6433
+188-1699-6168
+852-695-75415

APEX® 32022RV-80NT CBL B8 NF
Teknor Apex Company - Flexible Polyvinyl Chloride

Processing Information

Extrusion

Nominal Value Unit

Melt Temperature

340 to 360 °F

Notes

¹ Typical properties: these are not to be construed as specifications.

Revision Date: 8/9/2019

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.