

## APEX® 32043RV-55NT1 CBL B8 NP

Teknor Apex Company - Flexible Polyvinyl Chloride

Tuesday, August 27, 2019

General				
Material Status	Commercial: Active			
Availability	<ul><li> Africa &amp; Middle East</li><li> Asia Pacific</li></ul>	<ul><li>Europe</li><li>Latin America</li></ul>	North America	
Features	<ul> <li>BPA Free</li> <li>DOTP Blend Plasticizer</li> <li>E-beam Sterilizable</li> <li>Ethylene Oxide Sterilizable</li> </ul>	<ul> <li>Latex Free</li> <li>No Animal Derived Components</li> <li>Non-Phthalate - TOTM Plasticizer</li> <li>Non-Phthalate Plasticizer</li> </ul>	<ul> <li>Radiation (Gamma) Resistan</li> <li>Radiation Sterilizable</li> </ul>	
Agency Ratings	• EC 1907/2006 (REACH)	<ul> <li>OEHHA (California) Proposition 65</li> </ul>		
RoHS Compliance	<ul> <li>RoHS Compliant</li> </ul>			
Forms	Pellets			
Processing Method	Injection Molding			

<u>+135-3858-6433</u> +188-1699-6168 +852-695-75415

**General Information** 

ASTM & ISO Properties <sup>1</sup>				
Physical	Nominal Value	Unit	Test Method	
Density / Specific Gravity	1.15		ASTM D792	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength			ASTM D638	
50% Strain	260	psi		
100% Strain	450	psi		
300% Strain	1020	psi		
Tensile Strength (Break)	1370	psi	ASTM D638	
Tensile Elongation (Break)	430	%	ASTM D638	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness			ASTM D2240	
Shore A, 15 sec, Operating Stand	50			
Shore A, 15 sec, Hand Held	55			
Additional Information				

## Additional Information

-	
	EXAMPLE INJECTION MOLDING APPLICATIONS
	Adaptors
	Blood Pressure Bulbs
	Canulae
	Caps
	Connectors
	Drip/Sight Chambers
	Ear Protection
	Endotracheal Airway Cuffs
	Luers
	Mouthpieces
	Oxygen Masks
	Personal Safety Goggles
	Resuscitation Bags
	Suction Bulbs
	Syringe Bulbs
	Valves

Data Sheet Applies to Color(s) Listed Below: Clear Blue B8 NP (1136727)

## +135-3858-6433 +188-1699-6168 +852-695-75415

## APEX® 32043RV-55NT1 CBL B8 +852-695-7541

Teknor Apex Company - Flexible Polyvinyl Chloride

Processing Information			
Extrusion	Nominal Value Unit		
Melt Temperature	315 to 335 °F		

Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

Revision Date: 8/9/2019

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.