



## **APEX® 3300-60NT**

## Teknor Apex Company - Flexible Polyvinyl Chloride

Tuesday, August 27, 2019

| General Information |   |  |               |  |  |
|---------------------|---|--|---------------|--|--|
| General             |   |  |               |  |  |
| Material Status     | Commercial: Active  |  |               |  |  |
| Availability        | <ul><li> Africa &amp; Middle East</li><li> Asia Pacific</li></ul> | <ul><li>Europe</li><li>Latin America</li></ul> | North America |  |  |
| Additive            | Plasticizer   |  |               |  |  |
| Features            | DEHP Plasticizer  | Ethylene Oxide Sterilizable                    |               |  |  |
| Uses                | <ul> <li>Food Service Applications</li> </ul>                     | Medical/Healthcare Applications    Tubing      |               |  |  |
| Appearance          | Clear/Transparent   |  |               |  |  |
| Forms               | • Pellets   |  |               |  |  |
| Processing Method   | Extrusion   |  |               |  |  |

| ASTM & ISO Properties <sup>1</sup>   |               |      |             |  |
|--------------------------------------|---------------|------|-------------|--|
| Physical                             | Nominal Value | Unit | Test Method |  |
| Density / Specific Gravity           | 1.16          |      | ASTM D792   |  |
| Mechanical                           | Nominal Value | Unit | Test Method |  |
| Tensile Strength (100% Strain)       | 560           | psi  | ASTM D638   |  |
| Tensile Strength (Break)             | 1570          | psi  | ASTM D638   |  |
| Tensile Elongation (Break)           | 450           | %    | ASTM D638   |  |
| Hardness                             | Nominal Value | Unit | Test Method |  |
| Durometer Hardness (Shore A, 15 sec) | 60            |      | ASTM D2240  |  |
| Thermal                              | Nominal Value | Unit | Test Method |  |
| Brittleness Temperature              | -31.0         | °F   | ASTM D746   |  |

| Processing Information |                    |  |  |
|------------------------|--------------------|--|--|
| Extrusion              | Nominal Value Unit |  |  |
| Melt Temperature       | 335 °F             |  |  |

## **Notes**

Revision Date: 12/12/2013

<sup>&</sup>lt;sup>1</sup> Typical properties: these are not to be construed as specifications.