

APEX® 33022RV-50NT CBL B8 NP

Teknor Apex Company - Flexible Polyvinyl Chloride

Tuesday, August 27, 2019

| General Information | | | | |
|---------------------|--|---|---|--|
| General | | | | |
| Material Status | Commercial: Active | | | |
| Availability | Africa & Middle East Asia Pacific | Europe Latin America | North America | |
| Features | BPA FreeE-beam SterilizableEthylene Oxide Sterilizable | Latex FreeNo Animal Derived ComponentsNon-Phthalate - Citrate Plasticizer | Non-Phthalate Plasticizer Radiation (Gamma) Resistan Radiation Sterilizable | |
| Agency Ratings | • EC 1907/2006 (REACH) | OEHHA (California) Proposition 65 | | |
| RoHS Compliance | RoHS Compliant | | | |
| Forms | • Pellets | | | |
| Processing Method | Extrusion | | | |

| ASTM & ISO Properties ¹ | | | | |
|------------------------------------|---------------|------|-------------|--|
| Physical | Nominal Value | Unit | Test Method | |
| Density / Specific Gravity | 1.19 | | ASTM D792 | |
| Mechanical | Nominal Value | Unit | Test Method | |
| Tensile Strength | | | ASTM D638 | |
| 50% Strain | 225 | psi | | |
| 100% Strain | 400 | psi | | |
| 300% Strain | 1000 | psi | | |
| Tensile Strength (Break) | 1250 | psi | ASTM D638 | |
| Tensile Elongation (Break) | 410 | % | ASTM D638 | |
| Hardness | Nominal Value | Unit | Test Method | |
| Durometer Hardness | | | ASTM D2240 | |
| Shore A, 15 sec, Operating Stand | 46 | | | |
| Shore A, 15 sec, Hand Held | 50 | | | |
| A 1 1941 - 1 1 6 - 41 | | | | |

Additional Information

EXAMPLE EXTRUSION APPLICATIONS

Blood Pressure Tubing

Blood Transport & Delivery

Bubble Tubing

Cable Jacketing

Catheters

Dialysis Tubing

Drainage Tubing

Endotracheal Airway Tubing

Enteral Feeding Systems

Infusion Tubing

Oxygen Tubing

Peristaltic Pump Tubing

Suction Tubing

Data Sheet Applies to Color(s) Listed Below:

Clear Blue B8 NP (1136584)

+135-3858-6433 +188-1699-6168

APEX® 33022RV-50NT CBL B8 NF

Teknor Apex Company - Flexible Polyvinyl Chloride

| Processing Information | | |
|------------------------|--------------------|--|
| Extrusion | Nominal Value Unit | |
| Melt Temperature | 305 to 325 °F | |

Notes

Revision Date: 8/9/2019

¹ Typical properties: these are not to be construed as specifications.