

# APEX® 33022RV-65NT CBL B8 NP

Teknor Apex Company - Flexible Polyvinyl Chloride

Tuesday, August 27, 2019

## General Information

### General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• BPA Free • E-beam Sterilizable • Ethylene Oxide Sterilizable	• Latex Free • No Animal Derived Components • Non-Phthalate - Citrate Plasticizer	• Non-Phthalate Plasticizer • Radiation (Gamma) Resistant • Radiation Sterilizable
Agency Ratings	• EC 1907/2006 (REACH)	• OEHHA (California) Proposition 65	
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		
Processing Method	• Extrusion		

## ASTM & ISO Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.22		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
50% Strain	445	psi	
100% Strain	765	psi	
300% Strain	1710	psi	
Tensile Strength (Break)	2020	psi	ASTM D638
Tensile Elongation (Break)	390	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 15 sec, Operating Stand	60		
Shore A, 15 sec, Hand Held	65		

### Additional Information

#### EXAMPLE EXTRUSION APPLICATIONS

Blood Pressure Tubing  
 Blood Transport & Delivery  
 Bubble Tubing  
 Cable Jacketing  
 Catheters  
 Dialysis Tubing  
 Drainage Tubing  
 Endotracheal Airway Tubing  
 Enteral Feeding Systems  
 Infusion Tubing  
 Oxygen Tubing  
 Peristaltic Pump Tubing  
 Suction Tubing

Data Sheet Applies to Color(s) Listed Below:  
 CBL B8 NP (1136578)

**+135-3858-6433**  
**+188-1699-6168**  
**+852-695-75415**

**APEX® 33022RV-65NT CBL B8 NF**  
**Teknor Apex Company - Flexible Polyvinyl Chloride**

---

**Processing Information**

---

Extrusion	Nominal Value	Unit
Melt Temperature	320 to 340	°F

**Notes**

<sup>1</sup> Typical properties: these are not to be construed as specifications.

---

Revision Date: 8/9/2019

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.