

APEX® 33043RV-50NT1 CBL B8 NP

Teknor Apex Company - Flexible Polyvinyl Chloride

Tuesday, August 27, 2019

General			
Material Status	Commercial: Active		
Availability	 Africa & Middle East Asia Pacific	EuropeLatin America	North America
Features	 BPA Free DOTP Blend Plasticizer E-beam Sterilizable Ethylene Oxide Sterilizable 	 Latex Free No Animal Derived Components Non-Phthalate - TOTM Plasticizer Non-Phthalate Plasticizer 	 Radiation (Gamma) Resistan Radiation Sterilizable
Agency Ratings	EC 1907/2006 (REACH) OEHHA (California) Proposition 65		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Extrusion		

<u>+135-3858-6433</u> +188-1699-6168 +852-695-75415

General Information

ASTM & ISO Properties ¹				
Physical	Nominal Value	Unit	Test Method	
Density / Specific Gravity	1.14		ASTM D792	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength			ASTM D638	
50% Strain	245	psi		
100% Strain	440	psi		
300% Strain	1050	psi		
Tensile Strength (Break)	1400	psi	ASTM D638	
Tensile Elongation (Break)	450	%	ASTM D638	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness			ASTM D2240	
Shore A, 15 sec, Hand Held	50			
Shore A, 15 sec, Operating Stand	45			

EXAMPLE EXTRUSION APPLICATIONS: Blood Pressure Tubing Blood Transport & Delivery Bubble Tubing Cable Jacketing Catheters Dialysis Tubing Drainage Tubing Endotracheal Airway Tubing Enteral Feeding Systems Infusion Tubing Oxygen Tubing Peristaltic Pump Tubing Suction Tubing

Data Sheet Applies to Color(s) Listed Below: Clear Blue B8 NP (1136586)

+135-3858-6433 +188-1699-6168 +852-695-75415

APEX® 33043RV-50NT1 CBL B8 +852-695-7541

Teknor Apex Company - Flexible Polyvinyl Chloride

Processing Information			
Extrusion	Nominal Value Unit		
Melt Temperature	305 to 325 °F		

Notes

¹ Typical properties: these are not to be construed as specifications.

Revision Date: 8/9/2019

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.