

APEX® 33043RV-70NT1 CBL B8 NP

Teknor Apex Company - Flexible Polyvinyl Chloride

Tuesday, August 27, 2019

General Information

General

| | | | |
|-------------------|--|---|---|
| Material Status | • Commercial: Active | | |
| Availability | • Africa & Middle East • Asia Pacific | • Europe • Latin America | • North America |
| Features | • BPA Free • DOTP Blend Plasticizer • E-beam Sterilizable • Ethylene Oxide Sterilizable | • Latex Free • No Animal Derived Components • Non-Phthalate - TOTM Plasticizer • Non-Phthalate Plasticizer | • Radiation (Gamma) Resistant • Radiation Sterilizable |
| Agency Ratings | • EC 1907/2006 (REACH) | • OEHHA (California) Proposition 65 | |
| RoHS Compliance | • RoHS Compliant | | |
| Forms | • Pellets | | |
| Processing Method | • Extrusion | | |

ASTM & ISO Properties ¹

| Physical | Nominal Value | Unit | Test Method |
|----------------------------------|---------------|------|-------------|
| Density / Specific Gravity | 1.19 | | ASTM D792 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength | | | ASTM D638 |
| 50% Strain | 530 | psi | |
| 100% Strain | 880 | psi | |
| 300% Strain | 1780 | psi | |
| Tensile Strength (Break) | 2130 | psi | ASTM D638 |
| Tensile Elongation (Break) | 410 | % | ASTM D638 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness | | | ASTM D2240 |
| Shore A, 15 sec, Operating Stand | 64 | | |
| Shore A, 15 sec, Hand Held | 70 | | |

Additional Information

EXAMPLE EXTRUSION APPLICATIONS

Blood Pressure Tubing
 Blood Transport & Delivery
 Bubble Tubing
 Cable Jacketing
 Catheters
 Dialysis Tubing
 Drainage Tubing
 Endotracheal Airway Tubing
 Enteral Feeding Systems
 Infusion Tubing
 Oxygen Tubing
 Peristaltic Pump Tubing
 Suction Tubing

Data Sheet Applies to Color(s) Listed Below:
 Clear Blue B8 NP (1136670)

+135-3858-6433
+188-1699-6168
+852-695-75415

APEX® 33043RV-70NT1 CBL B8
Teknor Apex Company - Flexible Polyvinyl Chloride

Processing Information

| Extrusion | Nominal Value | Unit |
|------------------|----------------------|-------------|
| Melt Temperature | 325 to 345 | °F |

Notes

¹ Typical properties: these are not to be construed as specifications.

Revision Date: 8/9/2019

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.