

APEX® 3311-50NT

Teknor Apex Company - Flexible Polyvinyl Chloride

Tuesday, August 27, 2019

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• Plasticizer		
Features	• Ethylene Oxide Sterilizable	• Non-DEHP Plasticizer	
Uses	• Medical/Healthcare Applications	• Toys	• Tubing
Appearance	• Natural Color	• Opaque	
Forms	• Pellets		
Processing Method	• Extrusion		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.34		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (100% Strain)	360	psi	ASTM D638
Tensile Strength (Break)	1150	psi	ASTM D638
Tensile Elongation (Break)	410	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	50		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-54.4	°F	ASTM D746

Processing Information

Extrusion	Nominal Value	Unit
Melt Temperature	320	°F

Notes

¹ Typical properties: these are not to be construed as specifications.