



APEX® 4103

Teknor Apex Company - Flexible Polyvinyl Chloride

Wednesday, August 28, 2019

| | General I | nformation | | |
|--|--|----------------------------|-------|---------------------------|
| General | | | | |
| Material Status | Commercial: Active | | | |
| Availability | Africa & Middle East | Europe | | North America |
| | Asia Pacific | Latin America | | - North America |
| Uses | Connectors | • Plugs | | Wire & Cable Applications |
| | Grommets | Strain Reliefs | | |
| Wire Types | Molded Components | | | |
| Agency Ratings | • UL QMFZ2 | | | |
| RoHS Compliance | RoHS Compliant | | | |
| Appearance | Opaque | | | |
| Forms | • Pellets | | | |
| Processing Method | Injection Molding | | | |
| | ASTM & ISC | O Properties ¹ | | |
| Physical | | Nominal Value | Unit | Test Method |
| Density / Specific Gravity | | 1.38 | | ASTM D792 |
| Molding Shrinkage - Flow | | 0.010 to 0.012 | in/in | ASTM D955 |
| Mechanical | | Nominal Value | Unit | Test Method |
| Tensile Strength (Break) | | 1500 | psi | ASTM D638 |
| Tensile Elongation (Break) | | 220 | % | ASTM D638 |
| Hardness | | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A, 15 sec) | | 80 | | ASTM D2240 |
| Thermal | | Nominal Value | Unit | Test Method |
| Continuous Use Temperature | | 140 | °F | ASTM D794 |
| Brittleness Temperature | | -14.8 | °F | ASTM D746 |
| RTI Elec | | | | UL 746 |
| 0.03 in | | 194 | °F | |
| 0.12 in | | 194 | °F | |
| RTI Str | | | | UL 746 |
| 0.03 in | | 194 | °F | |
| 0.12 in | | 194 | °F | |
| Electrical | | Nominal Value | Unit | Test Method |
| Comparative Tracking Index (CTI) (0.118 in | າ) | PLC 0 | | UL 746 |
| High Amp Arc Ignition (HAI) (0.12 in) | | PLC 1 | | UL 746 |
| Hot-wire Ignition (HWI) (0.12 in) | | PLC 1 | | UL 746 |
| Flammability | | Nominal Value | Unit | Test Method |
| Flame Rating | | | | UL 94 |
| 0.03 in | | V-2 | | |
| 0.12 in | | V-0 | | |
| Oxygen Index | | 25 | % | ASTM D2863 |
| Additional Information | | | | |
| Temperature Rating: 60 °C | | | | |

Temperature Rating: 60 °C

Recognized Component, CSA C22.2 No. 0.6, CSA Flammability Classification: 0.6V-2 @ 0.86 mm

+135-3858-6433 +188-1699-6168 +852-695-75415

APEX® 4103

Teknor Apex Company - Flexible Polyvinyl Chloride

| Processing Information | | | |
|------------------------|--------------------|--|--|
| Injection | Nominal Value Unit | | |
| Processing (Melt) Temp | 355 °F | | |

Notes

Revision Date: 12/12/2013

¹ Typical properties: these are not to be construed as specifications.