

APEX® 4130

Teknor Apex Company - Flexible Polyvinyl Chloride

Wednesday, August 28, 2019

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Sunlight Resistant (720 hours) • UV Resistant		
Uses	• Flexible Cord Jacketing		
Wire Types	• SJT • SJTW	• SRDT • ST	• STW • SVT
Agency Ratings	• UL QMTT2		
RoHS Compliance	• RoHS Compliant		
Appearance	• Opaque		
Forms	• Pellets		
Processing Method	• Extrusion		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.39		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	2600	psi	ASTM D638
Tensile Elongation (Break)	360	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	83		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	167	°F	ASTM D794
Brittleness Temperature	-16.6	°F	ASTM D746
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	29	%	ASTM D2863

Additional Information

Prime suggestion
 Temperature Rating: 80 °C
 UL Sunlight Resistance Recognition: 720 hr
 Ultimate Elongation Retained, UL 1581, Oven Aged, 7 days, 113°C: 86 %
 Tensile Strength Retained, UL 1581, Oven Aged, 7 days, 113°C: 110 %

Processing Information

Extrusion	Nominal Value	Unit
Melt Temperature	355	°F

Notes

¹ Typical properties: these are not to be construed as specifications.

Revision Date: 12/12/2013

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.