



APEX® 55001

Teknor Apex Company - Flexible Polyvinyl Chloride

Wednesday, August 28, 2019

	,		110a00aay, 7 tagaat 20, 20 t		
General Information					
General					
Material Status	Commercial: Active				
Availability	 Africa & Middle East 	• Europe	North America		
	 Asia Pacific 	 Latin America 			
Features	Flame Retardant				
Uses	Communication Wire Jacketing				
Wire Types	• CL2R	• CMR	• MPR		
	• CL3R	• FPLR	• OFNR		
	NEC Article 725	NEC Article 800			
Agency Ratings	 NEC Article 760 	• UL 13	• UL 444		
	 NEC Article 770 	• UL 1424			
Appearance	 Opaque 				
Forms	• Pellets				
Processing Method	 Extrusion 				

ASTM & ISO Properties 1				
Physical	Nominal Value	Unit	Test Method	
Density / Specific Gravity	1.38		ASTM D792	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Break)	3000	psi	ASTM D638	
Tensile Elongation (Break)	360	%	ASTM D638	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A, 15 sec)	90		ASTM D2240	
Thermal	Nominal Value	Unit	Test Method	
Continuous Use Temperature	167	°F	ASTM D794	
Brittleness Temperature	-13.0	°F	ASTM D746	
Electrical	Nominal Value	Unit	Test Method	
Volume Resistivity	2.3E+12	ohms·cm	ASTM D257	
Flammability	Nominal Value	Unit	Test Method	
Oxygen Index	34	%	ASTM D2863	
A 1 PM 11 6 M				

Additional Information

Formerly Apex 82-E254-V Temperature Rating: 75 °C

UL Sunlight Resistance Recognition: No

Processing Information			
Extrusion	Nominal Value Unit		
Melt Temperature	375 °F		

Notes

¹ Typical properties: these are not to be construed as specifications.

Revision Date: 4/30/2019